

GROUP OF TESTING LABORATORIES GRYFITLAB

ul. Prosta 2, Łozienica, 72-100 Goleniów tel. (091) 431 82 42, fax (091) 418 97 57, kom. 607-900-481 www.gryfitlab.com, e-mail: contact@gryfitlab.com

Evidence of performance Airborne sound insulation of building components

Test Report

No. GLA-1277.1/16

Client

PRESS GLASS S.A. Nowa Wieś

ul. Kopalniana 9

42-262 Poczesna

Product:	Insulating glass unit			
Construction:	8,76Aku/12/6/12/12,76Aku			
Designation:	44.2 TH1,1 Phon class P2A / 12 / FL 6 / 12 / VSG (TH1,1 6 / 0,76 PVB SC / FL 6) class 1/B/1 Ar			
Dimension:	1230mm x 1480mm			
Gas filing:	Argon			
Cross-section:	8,76aku 12 6 12 12,76aku			

Rating	R _w (C; C _{tr})	STC	ОІТС
Basis	PN-EN ISO 717-1: 2013	ASTM E413-10	ASTM E1332-10
Value	48 (-3; -8) dB	48 dB	36 dB

Łozienica, 12.09.2016

PhD Krzysztof Mech
Head of Acoustics Laboratory