

Below physical values are belong only for sample production. In bulk production below values could be change.

ARTICLE CODE / NAME : 30777G / KENNA STAY BLACK

Date : 12.06.2023

COMPOSITION : 96%CO 4%LYCRA
WEAVE : 3/1 Z

COLOUR : REACT BLACK
FINISH : 002844

PARAMETER		CONDITION	UNIT	MIN	AVG	MAX	TEST METHOD
Weight		Unwashed	gr/m2	285	300	315	ASTM D3776
			oz/yd2	8,41	8,85	9,29	
		Washed (3*40HL)	gr/m2	309	325	341	
			oz/yd2	9,11	9,59	10,07	
Usable Width		Unwashed	cm	132,00	-	-	ASTM D3774
			inch	51,97	-	-	
Shrinkage	Warp	Washed (3*40HL)	%	0,00	-	-3,50	AATCC 135
	Weft	Washed (3*40HL)	%	-9,00	-	-13,00	
Skew Movement		Washed (3*40HL)	%	-3,00	-	3,00	LS&Co.Method2
Tear Strength	Warp	Washed (3*40HL)	grf	2.300,00	-	-	ASTM D1424
			lbs	5,07	-	-	
	Weft	Washed (3*40HL)	grf	1.900,00	-	-	
			lbs	4,19	-	-	
Tensile Strength	Warp	Washed (3*40HL)	kgf	50,00	-	-	ASTM D5034
			lbs	110,23	-	-	
	Weft	Washed (3*40HL)	kgf	20,00	-	-	
			lbs	44,09	-	-	
Elasticity	Weft	Washed (3*40HL)	%	42,00	-	52,00	ASTM D3107
	Warp	Washed (3*40HL)	%	-	-	-	
Growth	Weft	Washed (3*40HL)	%	-	7,00		ASTM D3107
	Warp	Washed (3*40HL)	%	-	7,00		
Seam Slippage	Warp	Washed (3*40HL)	kgf	-	-	-	ASTM D434 at 6,35 mm
	Weft	Washed (3*40HL)	kgf	-	-	-	
Ph		Unwashed		4,00	-	7,50	MORAPEX-A
Color Fastness	Dry	Unwashed	grey scale	3,00	-	-	AATCC 8
Crocking	Wet	Unwashed	gray scale	1-2	-	-	

CARE INSTRUCTION



INSPECTION 4 dp system

SHADE CONTROL Rinse Wash

REMARKS Please note that; heavy washing recipes (stone washes, heavy sand blast, heavy brushing-scrapping), use of bleach, permanganate or similar chemicals may cause problems. Therefore trials should be done before launching bulk production. If precautions are not taken, responsibility of the defects and shading differences belongs to the customer. There can be foreign fibers on fabric. CF to water and perspiration results are low.