

Below physical values are belong only for sample production. In bulk production below values could be change.

ARTICLE CODE / NAME : 74450D / KENNA HUNTER BLUE

Date : 12.06.2023

COMPOSITION : 96%CO 4%LYCRA	COLOUR : HUNTER BLUE
WEAVE : 3/1 Z	FINISH : 001321

PARAMETER		CONDITION	UNIT	MIN	AVG	MAX	TEST METHOD
Weight		Unwashed	gr/m2	276	290	305	ASTM D3776
			oz/yd2	8,12	8,55	8,98	
		Washed (3*60HL)	gr/m2	304	320	336	
			oz/yd2	8,97	9,44	9,91	
Usable Width		Unwashed	cm	132,00	-	-	ASTM D3774
			inch	51,97	-	-	
Shrinkage	Warp	Washed (3*60HL)	%	0,00	-	-3,50	AATCC 135
	Weft	Washed (3*60HL)	%	-10,00	-	-14,00	
Skew Movement		Washed (3*60HL)	%	-3,00	-	3,00	LS&Co.Method2
Tear Strength	Warp	Washed (3*60HL)	grf	3.000,00	-	-	ASTM D1424
			lbs	6,61	-	-	
	Weft	Washed (3*60HL)	grf	2.500,00	-	-	
			lbs	5,51	-	-	
Tensile Strength	Warp	Washed (3*60HL)	kgf	55,00	-	-	ASTM D5034
			lbs	121,25	-	-	
	Weft	Washed (3*60HL)	kgf	23,00	-	-	
			lbs	50,71	-	-	
Elasticity	Weft	Washed (3*60HL)	%	50,00	-	60,00	ASTM D3107
	Warp	Washed (3*60HL)	%	-	-	-	
Growth	Weft	Washed (3*60HL)	%	-	8,00		ASTM D3107
	Warp	Washed (3*60HL)	%	-	8,00		
Seam Slippage	Warp	Washed (3*60HL)	kgf	-	-	-	ASTM D434 at 6,35 mm
	Weft	Washed (3*60HL)	kgf	-	-	-	
Ph		Unwashed		4,00	-	7,50	MORAPEX-A
Color Fastness	Dry	Unwashed	grey scale	3,00	-	-	AATCC 8
Crocking	Wet	Unwashed	gray scale	1-2	-	-	

CARE INSTRUCTION 	INSPECTION 4 dp system
	SHADE CONTROL 30 Stone Wash

REMARKS Please note that; heavy washing recipes (stone washes, heavy sand blas t, heavy brushing-scrapping), use of bleach, permanganate or similar c hemicals may cause problems. Therefore trials should be done before la unching bulk production. If precautions are not taken, responsibility of the defects and shading differences belongs to the customer.