

9874B-39

WEAVE:

3/1 Z TWILL

COMPOSITION:

63ORCO16PSRPES11CMD6EME4EL

COLOR:

S.STAY BLACK

TREATMENT:

ALCHEMY

FINISH:

HIGHPOWERSTRETCH

CARE INSTRUCTIONS:

40°

P

* WASH, DRY AND IRON INSIDE OUT

** WASH AND DRY SEPARATELY

REMARKS

**

PLEASE DO NOT STONE WASH DUE TO MODAL BLEND.

ENZYME WASH OR IF REQUIRED PERLITE (SMALL STONES)

WASH IS RECOMMENDED. PLEASE DO NOT USE TOO MUCH

SOFTENER, SEAM SLIPPAGE MAY OCCUR.

**

DUE TO SPECIAL COTTON (RECYCLED; ORGANIC, ETC.)

USE, THERE IS COLORED FIBRE/UNDYED FIBRE FAULT

RISK

PROPERTY	UNIT	MIN	AVE	MAX	TEST METHOD	CONDITION
WEIGHT	gr/m^2 oz/yd^2	320.0 9,44	340.0 10,03	360.0 10,62	ASTM-D 3776	UNWASHED
WEIGHT	gr/m^2 oz/yd^2	370.0 10,91	390.0 11,5	410.0 12,09	ASTM-D3776	WASHED
WIDTH	cm inches	118.0 46,46	120.5 47,44	123.0 48,43	-	UNWASHED
SHRINKAGE WARP	%	-1	-2.5	-4	3HL (3X60'X60C')	WASHED
SHRINKAGE WEFT	%	-9	-11	-13	3HL (3X60'X60C')	WASHED
SKEW MOVEMENT	%	-3	0.1	3	AATCC 179	WASHED
TEAR STRENGTH WARP	g lb	4300.0 9,48			ASTM-D 1424	WASHED
TEAR STRENGTH WEFT	g lb	3300.0 7,28			ASTM-D 1424	WASHED
TENSILE STRENGTH WARP	kg lb	40.0 88,18			ASTM-D 5034-95	WASHED
TENSILE STRENGTH WEFT	kg lb	28.0 61,73			ASTM-D 5034-95	WASHED
CROCKING DRY	rating	3			AATCC-8-1996	UNWASHED
CROCKING WET	rating	1.5			AATCC-8-1996	UNWASHED
ELASTICITY	%	60	65	70	ASTM-D 3107-80 4LB	WASHED
GROWTH	%			7	ASTM-D 3107-80 4LB	WASHED
RECOVERY WEFT	%	87			ASTM-D 3107-80 4LB	WASHED
ELONGATION(WARP)	%	8	10	12	ASTM-D 5278-92	UNWASHED
PH	-	5	6.25	7.5	ISO3071 1980	-
LIGHT FASTNESS	scale	3			AATCC 16-1993	UNWASHED

K - Q
TSE-ISO-EN
9000

M - C
TSE - ISO
10002

C-6

TSE-ISO-EN
14000

TSE
TS-ISO
45001

TSE
TS-ISO-IEC-27001
BGYS

VeriCert

ISO 9001
VERI11011071

OEKO-TEX®

CONFIDENCE IN TEXTILES

STANDARD 100

60716601 Certenbel

Tested for harmful substances

www.oeko-tex.com/standard100

bettercotton™

member

Inspection:Visual 4DP system || Package:Sealed with polyethylen film by ultrasonic system

Created on: 2024-08-05 15:53:11.233