



Date:	16.10.2023	Status:	Under Development
Code:	DRS505891	Quality Control :	4 Point System
Type:	Denim Stretch Over Dyed	Weave:	3/1 B.T
Fabric Name:	ANWAR 10 STR BT BK/BK	Finishing:	O.D + H.S
Composition:	98.5CO + 1.5EA	Color:	Black * Black /0600
Shade Control:	Enzyme Wash 30min + Softener		

Physical Properties		Actual	Unit	Tolerance		Standards	Remarks
Weight		10.5	oz/y²	±5%		ASTM D3776 (2020)	Unwashed
Weight Washed		11	oz/y²	±5%		ASTM D3776 (2020)	Washed AATCC 135-2004(3x60HL)
Total Average Width		172	cm	-		ASTM D3774-18 (2024)	Unwashed
		67.7	inch	-			
Minimum Cuttable Width		167	cm	-		ASTM D3774-18 (2024)	Unwashed
		65.7	inch	-			
Shrinkage Warp		2.5	%	min. 0	max. 4	AATCC 135 (2004)	Washed (3x60HL)
Shrinkage Weft		7	%	±2		AATCC 135 (2004)	Washed (3x60HL)
Movement		0	%	±3		AATCC 179 (2004)	Washed (3x60HL)
Tear Warp	ELMENDORF	7250	g	min. 4710		ASTM D1424 (2021)	Washed (3x60HL)
		16	lbf	min. 10.4			
Tear Weft	ELMENDORF	4300	g	min. 2790		ASTM D1424 (2021)	Washed (3x60HL)
		9.5	lbf	min. 6.175			
Tensile Strength Warp		77110	g	min. 50120		ASTM D5034 (2021)	Washed (3x60HL)
		170	lbf	min. 110.5			
Tensile Strength Weft		31750	g	min. 20630		ASTM D5034 (2021)	Washed (3x60HL)
		70	lbf	min. 45.5			
Stiffness		1.5	KGF	±0.2		ASTM D4032 (2012)	Unwashed
Elasticity		20	%	min. 16	max. 24	ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Growth		4	%			ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Abrasion Resistance	MARTINDALE		rub/s	-		ISO 12947-2 (1998)	Max 20.000 Rubs or 2 Thread Breaks
Seam Slippage Warp			mm			ISO 13936-2 (120N)	Washed
Seam Slippage Weft			mm				
Pilling Tendency	MARTINDALE		-			ISO 12945-2 (2000)	Washed
pH		6	-	min. 4.5	max. 7.5	ISO 3071: (2020)	
Crocking Dry (Rubbing)		3	-			ISO 105-X12 (2001)	Unwashed
Crocking Wet		1	-			ISO 105-X12 (2001)	Unwashed

Care Instructions

Wash	Iron	Chlorinate	Dry clean	Temporal Dry

Notes :

- The roll length is measured by calibrated inspection with machines tolerance ± 1% : ISO 3933:1976.
- Please inspect before cutting, no claims acceptable after cutting.
- Please note that heavy washing recipes (stone washes, heavy brushing-scrapping, and use of bleach or similar chemicals) may cause problems, Therefore the customer should do the washing trials before bulk production.
- Please be informed that we cannot accept any claim after six Months from invoice issuing date.
- Above physical values belong only for sample production, In bulk production values could be changed.

