



OFFICE

Huzur Mahallesi Cendere Caddesi
No: 114 B Blok Kat:26 No:377
Skyland Sarıyer İstanbul Turkey
PostCode: 34396
P. +90 212 465 80 99 | Ext
F. +90 212 465 82 32
MILL
Public Free Zone Damietta Egypt
P. +20 57 229 23 30
F. +20 57 229 23 31

MILL

Public Free Zone
Damietta, EGYPT
P: +20 (57) 229 23 30 Pbx
F: +20 (57) 229 2331 Pbx

TEMPORARY FABRIC SPECIFICATION

ARTICLE NAME : ARDEN TOPBLUE

PDR Name : 115506

DATE : 03-08-2024

SHORT CODE : T6216G

CONSTRUCTION			QUALITY CONTROL			
WEAVE	3/1 LHT		QUALITY CONTROL SYSTEM		4 POINT SYSTEM	
COMPOSITION	%95CO %2EL %3EME		SHADE CONTROL SYSTEM		555	
Note			SHADE CONTROL RECIPE		STONE WASH 35 MIN	
PHYSICAL	Test Method	units	MIN	AVG	MAX	REMARKS
WEIGHT	ASTM D3776	gm/m2 ouns/yd2	338 9.97	355 10.50	374 11.05	RAW FABRIC
WEIGHT	ASTM D3776	gm/m2 ouns/yd2	387 11.40	406 12.00	427 12.59	1*90 HL
USABLE WIDTH		Cm	155			RAW FABRIC
SHRINKAGE Warp	ISO 6330	%	-1		-4	1*90 HL
SHRINKAGE Weft	ISO 6330	%	-10		-14	1*90 HL
SKEW MOVEMENT	LS&CO Method 2	%	-3		3	1*90 HL
TEAR STRENGTH Warp	ASTM D1424	gm	4300			1*90 HL
TEAR STRENGTH Weft	ASTM D1424	gm	3300			1*90 HL
TENSILE STRENGTH Warp	ASTM D5034	kg	65			1*90 HL
TENSILE STRENGTH Weft	ASTM D5034	kg	35			1*90 HL
STIFFNESS	ASTM D4032	kg		N/A		RAW FABRIC
WARP ELONGATION	ASTM D3107	%		N/A		RAW FABRIC
WARP ELASTICITY	ASTM D3107	%		N/A		1*90 HL
WEFT ELASTICITY	ASTM D3107	%	30		36	1*90 HL
WARP GROWTH	ASTM D3107	%		N/A		1*90 HL
WEFT GROWTH	ASTM D3107	%			6	1*90 HL
SEAM SLIPPAGE (Warp x Weft)	ASTM D1683	kg		N/A		1*90 HL
pH	ISO 3071/Morapex	Value	4.5		7.5	RAW FABRIC
COLOUR FASTNESS	Test Method	units	MIN	AVG	MAX	REMARKS
CROCKING Dry	AATCC 8	rating	3			RAW FABRIC
CROCKING Wet	AATCC 8	rating	1.5			RAW FABRIC
VISUAL	Test Method	units	MIN	AVG	MAX	REMARKS
Dp/100m2		dP		14	20	
Major Defects/100m		#defects			5	
Piece Length		Mt	15			
Roll Length		Mt	30			
#Piece / Roll		pcs			3	
Max SHADE(for 0<>5000 mt shipments)		Value			4	
Max SHADE(for 5000<>10000mt shipm)		Value			6	
Max SHADE(for 10000< mt shipments)		Value			8	
Care Instructions		Certifications				
Fabric: Fabric is sensitive to Resin & Selulaz Enzymes.Before bulk was		 ISO 9001:2015 ISO 14001:2015 OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 71048 OETI Tested for harmful substances. www.oeko-tex.com/standard100				
Garment: Fabric is sensitive to Resin & Selulaz Enzymes. Before bulk wash, pls make sampling.						