



Code:	DRB504739	Quality Control :	4 Point System
Type:	Denim Recycled Stretch Blended	Weave:	3/1 Z
Fabric Name:	BOOM 40 ANTH	Finishing:	Pre Wash + H.S
Composition:	82CO + 16Recycled Post-Consumer PES + 2EA	Color:	Anthracite Grey /6
Shade Control:	Enzyme wash 30min	Color Note:	Such a color is subject to a wide range of shade variation

Physical Properties		Actual	Unit	Tolerance		Standards	Remarks
Weight		9.75	oz/y²	±5%		ASTM D3776 (2020)	Unwashed
Weight Washed		10.75	oz/y²	±5%		ASTM D3776 (2020)	Washed AATCC 135-2004(3x60HL)
Total Average Width		157	cm	-		ASTM D3774-18 (2024)	Unwashed
		61.8	inch	-			
Minimum Cuttable Width		152	cm	-		ASTM D3774-18 (2024)	Unwashed
		59.8	inch	-			
Shrinkage Warp		2.5	%	min. 0	max. 4	AATCC 135 (2004)	Washed (3x60HL)
Shrinkage Weft		10	%	±2		AATCC 135 (2004)	Washed (3x60HL)
Movement		0	%	±3		AATCC 179 (2004)	Washed (3x60HL)
Tear Warp	ELMENDORF	5890	g	min. 3820		ASTM D1424 (2021)	Washed (3x60HL)
		13	lbf	min. 8.45			
Tear Weft	ELMENDORF	4980	g	min. 3230		ASTM D1424 (2021)	Washed (3x60HL)
		11	lbf	min. 7.15			
Tensile Strength Warp		77110	g	min. 50120		ASTM D5034 (2021)	Washed (3x60HL)
		170	lbf	min. 110.5			
Tensile Strength Weft		34020	g	min. 22110		ASTM D5034 (2021)	Washed (3x60HL)
		75	lbf	min. 48.75			
Stiffness		1	KGF	±0.2		ASTM D4032 (2012)	Unwashed
Elasticity		35	%	min. 31	max. 39	ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Growth		3.5	%			ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Abrasion Resistance	MARTINDALE		rub/s	-		ISO 12947-2 (1998)	Max 20.000 Rubs or 2 Thread Breaks
Seam Slippage Warp			mm			ISO 13936-2 (120N)	Washed
Seam Slippage Weft			mm				
Pilling Tendency	MARTINDALE		-			ISO 12945-2 (2000)	Washed
pH		6	-	min. 4.5	max. 7.5	ISO 3071: (2020)	
Crocking Dry (Rubbing)		4	-			ISO 105-X12 (2001)	Unwashed
Crocking Wet		2	-			ISO 105-X12 (2001)	Unwashed

Care Instructions

Wash	Iron	Chlorinate	Dry clean	Temporal Dry

Notes :

- The roll length is measured by calibrated inspection with machines tolerance ± 1% : ISO 3933:1976.
- Please inspect before cutting, no claims acceptable after cutting.
- Please note that heavy washing recipes (stone washes, heavy brushing-scrapping, and use of bleach or similar chemicals) may cause problems, Therefore the customer should do the washing trials before bulk production.
- Please be informed that we cannot accept any claim after six Months from invoice issuing date.

