



Date:	30-JUL-2023	Status:	Under Development
Code:	DRB505704	Quality Control:	4 Point System
Type:	Denim Recycled Stretch Blended Over Dyed	Weave:	3/1 Z
Fabric Name:	BOOM /RS OCEAN O.D	Finishing:	O.D + RS + H.S Using the enzyme loses the brushing effect
Composition:	82CO + 16Recycled Post-Consumer PES + 2EA	Color:	Ocean Blue /7.5 * Black /0605
Shade Control:	Enzyme wash 30min		

Physical Properties		Actual	Unit	Tolerance	Standards	Remarks
Weight Dry		10.5	oz/y2	±5%	ASTM D3776 (2020)	Raw Fabric
Weight Washed		11.75	oz/y2	±5%	ASTM D3776 (2020)	Washed AATCC 135-2004(3x60HL)
Total Average Width		150	cm	-	ASTM D3774-18 (2024)	Raw Fabric
		59.1	inch	-		
Minimum Cuttable Width		145	cm	-	ASTM D3774-18 (2024)	Raw Fabric
		57.1	inch	-		
Shrinkage Warp		2.5	%	min. 0 - max. 4	AATCC 135 (2004)	Washed (3x60HL)
Shrinkage Weft		13	%	±2	AATCC 135 (2004)	Washed (3x60HL)
Movement		0	%	±3	AATCC 179 (2004)	Washed (3x60HL)
Tear Warp - ELMENDROF		5670	g	min. 3680	ASTM D1424 (2020)	Washed (3x60HL)
		12.5	lbf	min. 8.125		
Tear Weft - ELMENDROF		4080	g	min. 2650	ASTM D1424 (2020)	Washed (3x60HL)
		9	lbf	min. 5.85		
Tensil Strength Warp		81640	g	min. 53060	ASTM D5034 (2021)	Washed (3x60HL)
		180	lbf	min. 117		
Tensil Strength Weft		36280	g	min. 23580	ASTM D5034 (2021)	Washed (3x60HL)
		80	lbf	min. 52		
Stiffness		1.8	KGF	±0.2	ASTM D4032 (2012)	Raw Fabric
Elasticity		40	%	min. 36 - max. 44	ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Growth		4	%	-	ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Abrasion Resistance - MARTINDALE			rubs	-	ISO 12947-2 (1998)	Max 20.000 Rubs or 2 Thread Breaks
Seam Slippage Warp			N	-	ISO 13936-1 (6mm)	Washed
Seam Slippage Weft			N	-	ISO 13936-1 (6mm)	Washed
Pilling Tendency - MARTINDALE			-	-	ISO 12945-2 (2000)	Washed
PH		6	-	min. 4.5 - max. 7.5	ISO 3071 (2020)	
Crocking Dry(Rubbing)		'0'	-		ISO 105-X12 (2001)	Raw Fabric
Crocking Wet		'0'	-		ISO 105-X12 (2001)	Raw Fabric
Wash	Iron		Chlorinate		Dry clean	Temporal Dry

Notes:

- The roll length is measured by calibrated inspection with machines tolerance $\pm 1\%$: ISO 3933:1976.
- Please inspect before cutting, no claims acceptable after cutting.
- Please note that heavy washing recipes (stone washes, heavy brushing-scrapping, and use of bleach or similar chemicals) may cause problems, Therefore the customer should do the washing trials before bulk production.
- Please be informed that we cannot accept any claim after six Months from invoice issuing date.
- Above physical values belong only for sample production, In bulk production values could be changed.

