

Date:	13.04.2022	Status:	Under Development
Code:	DRB504549	Quality Control system:	4 Point System
Type:	Denim Recycled Stretch Blended Over Dyed	Weave:	3/1 Z
Fabric Name:	BOOM 40 OCEAN O.D	Finishing:	O.D + H.S
Composition:	82CO + 16Recycled Post-Consumer PES + 2EA	Color:	Ocean Blue /7.5 * Black /0605
Shade Control:	Enzyme wash 30min		

Physical Properties		Actual	Unit	Tolerance		Standards	Remarks
Weight		9.75	oz/y²	±5%		ASTM D3776 (2013)	Unwashed
Weight Washed		10.75	oz/y²	±5%		ASTM D3776 (2013)	Washed AATCC 135-2004(3x60HL)
Total Average Width		157	cm	-		ASTM D3774 (2012)	Unwashed
		61.8	inch	-			
Minimum Cuttable Width		151	cm	-		ASTM D3774 (2012)	Unwashed
		59.4	inch	-			
Shrinkage Warp		2.5	%	min. 0	max. 4	AATCC 135 (2004)	Washed (3x60HL)
Shrinkage Weft		11	%	±2		AATCC 135 (2004)	Washed (3x60HL)
Movement		0	%	±3		AATCC 179 (2004)	Washed (3x60HL)
Tear Warp	ELMENDORF	6350	g	min. 4120		ASTM D1424 (2013)	Washed (3x60HL)
		14	lbf	min. 9.1			
Tear Weft	ELMENDORF	4980	g	min. 3230		ASTM D1424 (2013)	Washed (3x60HL)
		11	lbf	min. 7.15			
Tensile Strength Warp		77110	g	min. 50120		ASTM D5034 (2013)	Washed (3x60HL)
		170	lbf	min. 110.5			
Tensile Strength Weft		34020	g	min. 22110		ASTM D5034 (2013)	Washed (3x60HL)
		75	lbf	min. 48.75			
Stiffness		1.4	KGF	±0.2		ASTM D4032 (2012)	Unwashed
Elasticity		35	%	min. 31	max. 39	ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Growth		4	%			ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Abrasion Resistance	MARTINDALE		rub/s	-		ISO 12947-2 (1998)	Max 20.000 Rubs or 2 Thread Breaks
Seam Slippage			-			ISO 13936-2	Washed
Pilling Tendency	MARTINDALE		-			ISO 12945-2 (2000)	Washed
pH		6	-	min. 4.5	max. 7.5	ISO 3071: (2020)	
Crocking Dry(Rubbing)		3-4	-			ISO 105-X12 (2001)	Unwashed
Crocking Wet		1-2	-			ISO 105-X12 (2001)	Unwashed

Care Instructions

Wash	Iron	Chlorinate	Dry clean	Temporal Dry
				

Notes :

- The roll length is measured by calibrated inspection with machines tolerance ± 1% : ISO 3933:1976.
- Please inspect before cutting, no claims acceptable after cutting.
- Please note that heavy washing recipes (stone washes, heavy brushing-scraping, and use of bleach or similar chemicals) may cause problems, Therefore the customer should do the washing trials before bulk production.
- Please be informed that we cannot accept any claim after six Months from invoice issuing date.
- Above physical values belong only for sample production, In bulk production values could be changed.

