



DNM TEXTILE SPINNING, WEAVING and DYEING

OFFICE

Huzur Mahallesi Cendere Caddesi
No: 114 B Blok Kat:26 No:377
Skyland Sarıyer İstanbul Turkey
PostCode. 34396
P. +90 212 465 80 99 | Ext
F. +90 212 465 82 32
MILL
Public Free Zone Damietta Egypt
P. +20 57 229 23 30
F. +20 57 229 23 31

MILL

Public Free Zone
Damietta, EGYPT
P: +20 (57) 229 23 30 Pbx
F: +20 (57) 229 2331 Pbx

FABRIC SPECIFICATION

DATE : 27-07-2021

SHORT CODE : M84659A

ARTICLE NAME : CASPIAN SHINYBLUE

CONSTRUCTION

WEAVE	3/1 RHT	WARP NE	8.22
Note		WEFT NE	12.97
COLOR	SHINYBLUE	WARP DENSITY(end/cm)	31.25
COMPOSITION	%94CO %2EL %4EME	WEFT DENSITY(fill/cm)	19.9

PHYSICAL	Test Method	units	MIN	AVG	MAX	REMARKS
WEIGHT	ASTM D3776	gm/m2 ouns/yd2	346 10.20	364 10.75	383 11.30	RAW FABRIC
WEIGHT	ASTM D3776	gm/m2 ouns/yd2	403 11.88	423 12.50	445 13.10	1*90 HL
USABLE WIDTH		Cm	150			RAW FABRIC
SHRINKAGE Warp	ISO 6330	%	-1		-4	1*90 HL
SHRINKAGE Weft	ISO 6330	%	-13		-17	1*90 HL
TEAR STRENGTH Warp	ASTM D1424	gm	4300			1*90 HL
TEAR STRENGTH Weft	ASTM D1424	gm	2800			1*90 HL
TENSILE STRENGTH Warp	ASTM D5034	kg	65			1*90 HL
TENSILE STRENGTH Weft	ASTM D5034	kg	30			1*90 HL
WARP ELASTICITY	ASTM D3107	%		N/A		1*90 HL
WEFT ELASTICITY	ASTM D3107	%	30		38	1*90 HL
WARP GROWTH	ASTM D3107	%		N/A		1*90 HL
WEFT GROWTH	ASTM D3107	%			6	1*90 HL
VISUAL	Test Method	units	MIN	AVG	MAX	REMARKS
Dp/100m2		dP		14	20	
Major Defects/100m		#defects			5	
Piece Length		Mt	15			
Roll Length		Mt	30			
#Piece / Roll		pcs			3	
Max SHADE(for 0<>5000 mt shipments)		Value			4	
Max SHADE(for 5000<>10000mt shipm)		Value			6	
Max SHADE(for 10000< mt shipments)		Value			8	

OFFICE

Huzur Mahallesi Cendere Caddesi
No: 114 B Blok Kat:26 No:377
Skyland Sarıyer İstanbul Turkey
PostCode. 34396
P. +90 212 465 80 99 | Ext
F. +90 212 465 82 32
MILL
Public Free Zone Damietta Egypt
P. +20 57 229 23 30
F. +20 57 229 23 31

MILL

Public Free Zone
Damietta, EGYPT
P: +20 (57) 229 23 30 Pbx
F: +20 (57) 229 2331 Pbx

FABRIC SPECIFICATION

DATE : 27-07-2021
SHORT CODE : M84659A
ARTICLE NAME : CASPIAN SHINYBLUE

CONSTRUCTION

WEAVE	3/1 RHT	WARP NE	8.22
Note		WEFT NE	12.97
COLOR	SHINYBLUE	WARP DENSITY(end/cm)	31.25
COMPOSITION	%94CO %2EL %4EME	WEFT DENSITY(fill/cm)	19.9
QUALITY CONTROL			REMARKS
QUALITY CONTROL SYSTEM		4 POINT SYSTEM	
SHADE CONTROL SYSTEM		555	
SHADE CONTROL RECIPE		STONE WASH 35 MIN	
Care Instructions		Certifications	
Fabric:		   	
Garment:		 	
		87947	