

OFFICE

Huzur Mahallesi Cendere Caddesi
No: 114 B Blok Kat:26 No:377
Skyland Sarıyer İstanbul Turkey
PostCode. 34396
P. +90 212 465 80 99 | Ext
F. +90 212 465 82 32
MILL
Public Free Zone Damietta Egypt
P. +20 57 229 23 30
F. +20 57 229 23 31

MILL

Public Free Zone
Damietta, EGYPT
P: +20 (57) 229 23 30 Pbx
F: +20 (57) 229 2331 Pbx

TEMPORARY FABRIC SPECIFICATION

ARTICLE NAME : CORBETT ATLANTICBLUE_RGN50

PDR Name : 112897

DATE : 10-03-2025

SHORT CODE : M65410T

CONSTRUCTION			QUALITY CONTROL			
WEAVE	3/1 RHT		QUALITY CONTROL SYSTEM			4 POINT SYSTEM
COMPOSITION	%77CO %3EL %13CLY %7EME		SHADE CONTROL SYSTEM			555
Note			SHADE CONTROL RECIPE			STONE WASH 35 MIN
PHYSICAL	Test Method	units	MIN	AVG	MAX	REMARKS
WEIGHT	ASTM D3776	gm/m2 ouns/yd2	290 8.55	305 9.00	320 9.45	RAW FABRIC
WEIGHT	ASTM D3776	gm/m2 ouns/yd2	306 9.00	322 9.50	338 9.97	1*90 HL
USABLE WIDTH		Cm	125			RAW FABRIC
SHRINKAGE Warp	ISO 6330	%	-1		-4	1*90 HL
SHRINKAGE Weft	ISO 6330	%	-7		-11	1*90 HL
SKEW MOVEMENT	LS&CO Method 2	%	-3		3	1*90 HL
TEAR STRENGTH Warp	ASTM D1424	gm	4000			1*90 HL
TEAR STRENGTH Weft	ASTM D1424	gm	2800			1*90 HL
TENSILE STRENGTH Warp	ASTM D5034	kg	55			1*90 HL
TENSILE STRENGTH Weft	ASTM D5034	kg	30			1*90 HL
STIFFNESS	ASTM D4032	kg		N/A		RAW FABRIC
WARP ELONGATION	ASTM D3107	%		N/A		RAW FABRIC
WARP ELASTICITY	ASTM D3107	%		N/A		1*90 HL
WEFT ELASTICITY	ASTM D3107	%	46		54	1*90 HL
WARP GROWTH	ASTM D3107	%		N/A		1*90 HL
WEFT GROWTH	ASTM D3107	%			8	1*90 HL
SEAM SLIPPAGE (Warp x Weft)	ASTM D1683	kg		N/A		1*90 HL
pH	ISO 3071/Morapex	Value	4.5		7.5	RAW FABRIC
COLOUR FASTNESS	Test Method	units	MIN	AVG	MAX	REMARKS
CROCKING Dry	AATCC 8	rating	3			RAW FABRIC
CROCKING Wet	AATCC 8	rating	1.5			RAW FABRIC
VISUAL	Test Method	units	MIN	AVG	MAX	REMARKS
Dp/100m2		dP		14	20	
Major Defects/100m		#defects			5	
Piece Length		Mt	15			
Roll Length		Mt	30			
#Piece / Roll		pcs			3	
Max SHADE(for 0<>5000 mt shipments)		Value			4	
Max SHADE(for 5000<>10000mt shipm		Value			6	
Max SHADE(for 10000< mt shipments)		Value			8	
Care Instructions		Certifications				
Fabric:		 Deutsche Akkreditierungsstelle D-NN-18149-01-00 ISO 9001:2015	 71048 OETI Tested for harmful substances. www.oeko-tex.com/standard100	 ACCREDITED Management Systems Certification Body UKAS 27001		
tencel is sensitive to stone, before stone wash, pls try & see or						
Garment:						
tencel is sensitive to stone, before stone wash, pls try & see on a small batch						