



OFFICE
Huzur Mahallesi Cendere Caddesi
No: 114 B Blok Kat:26 No:377
Skyland Sariyer Istanbul Turkey
PostCode: 34396
P. +90 212 465 80 99 | Ext
F. +90 212 465 82 32
MILL
Public Free Zone Damietta Egypt
P. +20 57 229 23 30
F. +20 57 229 23 31

MILL
Public Free Zone
Damietta, EGYPT
P: +20 (57) 229 23 30 Pbx
F: +20 (57) 229 2331 Pbx

TEMPORARY FABRIC SPECIFICATION

ARTICLE NAME : D1005-C STR L1

PDR Name : 107649

DATE : 25/04/2024

SHORT CODE : T3529L

CONSTRUCTION			QUALITY CONTROL			
WEAVE	3/1 RHT		QUALITY CONTROL SYSTEM		4 POINT SYSTEM	
COMPOSITION	%94CO %2EL %4EME		SHADE CONTROL SYSTEM		555	
Note			SHADE CONTROL RECIPE		STONE WASH 35 MIN	
PHYSICAL	Test Method	units	MIN	AVG	MAX	REMARKS
WEIGHT	ASTM D3776	gm/m2 ouns/yd2	362 10.68	381 11.25	400 11.80	RAW FABRIC
WEIGHT	ASTM D3776	gm/m2 ouns/yd2	427 12.59	449 13.25	472 13.92	1*90 HL
USABLE WIDTH		Cm	145			RAW FABRIC
SHRINKAGE Warp	ISO 6330	%	-1		-4	1*90 HL
SHRINKAGE Weft	ISO 6330	%	-11		-15	1*90 HL
SKEW MOVEMENT	LS&CO Method 2	%	-3		3	1*90 HL
TEAR STRENGTH Warp	ASTM D1424	gm		N/A		1*90 HL
TEAR STRENGTH Weft	ASTM D1424	gm		N/A		1*90 HL
TENSILE STRENGTH Warp	ASTM D5034	kg		N/A		1*90 HL
TENSILE STRENGTH Weft	ASTM D5034	kg		N/A		1*90 HL
STIFFNESS	ASTM D4032	kg		N/A		RAW FABRIC
WARP ELONGATION	ASTM D3107	%		N/A		RAW FABRIC
WARP ELASTICITY	ASTM D3107	%		N/A		1*90 HL
WEFT ELASTICITY	ASTM D3107	%	30		38	1*90 HL
WARP GROWTH	ASTM D3107	%		N/A		1*90 HL
WEFT GROWTH	ASTM D3107	%		N/A		1*90 HL
SEAM SLIPPAGE (Warp x Weft)	ASTM D1683	kg		N/A		1*90 HL
pH	ISO 3071/Morapex	Value	4.5		7.5	RAW FABRIC
COLOUR FASTNESS	Test Method	units	MIN	AVG	MAX	REMARKS
CROCKING Dry	AATCC 8	rating	3			RAW FABRIC
CROCKING Wet	AATCC 8	rating	1.5			RAW FABRIC
VISUAL	Test Method	units	MIN	AVG	MAX	REMARKS
Dp/100m2		dP		14	20	
Major Defects/100m		#defects			5	
Piece Length		Mt	15			
Roll Length		Mt	30			
#Piece / Roll		pcs			3	
Max SHADE(for 0<>5000 mt shipments)		Value			4	
Max SHADE(for 5000<>10000mt shipm		Value			6	
Max SHADE(for 10000< mt shipments)		Value			8	
Care Instructions		Certifications				
Fabric: Due to light weight of the fabric, heavy stone wash may cause		   				
Garment: Due to light weight of the fabric, heavy stone wash may cause strength problems. Please make your tests and see on a small batch.						