

OFFICE

Huzur Mahallesi Cendere Caddesi
No: 114 B Blok Kat:26 No:377
Skyland Saryyer İstanbul Turkey
PostCode. 34396
P. +90 212 465 80 99 | Ext
F. +90 212 465 82 32
MILL
Public Free Zone Damietta Egypt
P. +20 57 229 23 30
F. +20 57 229 23 31

MILL

Public Free Zone
Damietta, EGYPT
P: +20 (57) 229 23 30 Pbx
F: +20 (57) 229 2331 Pbx

FABRIC SPECIFICATION

DATE : 12-03-2024

SHORT CODE : S12961D

ARTICLE NAME : DOUGLAS BLACK OD BLACK

CONSTRUCTION

WEAVE	3/1 RHT	WARP NE	7.32
Note		WEFT NE	9.91
COLOR	NERO	WARP DENSITY(end/cm)	29
COMPOSITION	%99CO %1EL	WEFT DENSITY(fill/cm)	18.71

PHYSICAL	Test Method	units	MIN	AVG	MAX	REMARKS
WEIGHT	ASTM D3776	gm/m2 ouns/yd2	370 10.91	389 11.50	409 12.05	RAW FABRIC
WEIGHT	ASTM D3776	gm/m2 ouns/yd2	403 11.88	423 12.50	445 13.10	1*90 HL
USABLE WIDTH		Cm	155			RAW FABRIC
SHRINKAGE Warp	ISO 6330	%	-1		-4	1*90 HL
SHRINKAGE Weft	ISO 6330	%	-9		-12	1*90 HL
TEAR STRENGTH Warp	ASTM D1424	gm	4300			1*90 HL
TEAR STRENGTH Weft	ASTM D1424	gm	3300			1*90 HL
TENSILE STRENGTH Warp	ASTM D5034	kg	65			1*90 HL
TENSILE STRENGTH Weft	ASTM D5034	kg	40			1*90 HL
ELASTICITY	ASTM D3107	%	24		30	1*90 HL
GROWTH	ASTM D3107	%	3		6	1*90 HL

VISUAL	Test Method	units	MIN	AVG	MAX	REMARKS
Dp/100m2		dP		14	20	
Major Defects/100m		#defects			5	
Piece Length		Mt	15			
Roll Length		Mt	30			
#Piece / Roll		pcs			3	
Max SHADE(for 0<>5000 mt shipments)		Value			4	
Max SHADE(for 5000<>10000mt shipm		Value	3		6	
Max SHADE(for 10000< mt shipments)		Value			8	

QUALITY CONTROL

QUALITY CONTROL		REMARKS
QUALITY CONTROL SYSTEM	4 POINT SYSTEM	
SHADE CONTROL SYSTEM	555	
SHADE CONTROL RECIPE	ENZYME WASH 10 MIN	

Care Instructions

Fabric:

**Garment:**

inside out, vastness beyond



101422