



OFFICE
Huzur Mahallesi Cendere Caddesi
No: 114 B Blok Kat:26 No:377
Skyland Sariyer Istanbul Turkey
PostCode: 34396
P. +90 212 465 80 99 | Ext
F. +90 212 465 82 32
MILL
Public Free Zone Damietta Egypt
P. +20 57 229 23 30
F. +20 57 229 23 31

MILL
Public Free Zone
Damietta, EGYPT
P: +20 (57) 229 23 30 Pbx
F: +20 (57) 229 2331 Pbx

FABRIC SPECIFICATION

ARTICLE NAME : DOUGLAS SHINNYBLUE OD BROWN PRD NO : 104389
SAMPLE NAME : C1477-A STR OD BROWN COLOR: : SHINYBLUE DATE:12/03/2024

CONSTRUCTION		QUALITY CONTROL	
WEAVE	3/1 RHT	QUALITY CONTROL SYSTEM	4 POINT SYSTEM
COMPOSITION	%99CO %1EL	SHADE CONTROL SYSTEM	555
NOTE		SHADE CONTROL RECIPE	ENZYME WASH 10 MIN

PHYSICAL	Test Method	units	MIN	AVG	MAX	REMARKS
WEIGHT	ASTM D3776	gm/m2 ouns/yd2	370 10.91	389 11.50	409 12.05	RAW FABRIC
WEIGHT	ASTM D3776	gm/m2 ouns/yd2	403 11.88	423 12.50	445 13.10	1*90 HL
USABLE WIDTH		Cm	155			RAW FABRIC
SHRINKAGE Warp	ISO 6330	%	-1		-4	1*90 HL
SHRINKAGE Weft	ISO 6330	%	-9		-12	1*90 HL
SKEW MOVEMENT	LS&CO Method 2	%	-3		3	1*90 HL
TEAR STRENGTH Warp	ASTM D1424	gm	4300			1*90 HL
TEAR STRENGTH Weft	ASTM D1424	gm	3300			1*90 HL
TENSILE STRENGTH Warp	ASTM D5034	kg	65			1*90 HL
TENSILE STRENGTH Weft	ASTM D5034	kg	40			1*90 HL
STIFFNESS	ASTM D4032	kg		N/A		RAW FABRIC
WARP ELONGATION	ASTM D3107	%		N/A		RAW FABRIC
WARP ELASTICITY	ASTM D3107	%		N/A		1*90 HL
WEFT ELASTICITY	ASTM D3107	%	24		30	1*90 HL
WARP GROWTH	ASTM D3107	%		N/A		1*90 HL
WEFT GROWTH	ASTM D3107	%	3		6	1*90 HL
SEAM SLIPPAGE (Warp x Weft)	ASTM D1683	kg		N/A		1*90 HL
pH	ISO 3071/Morapex	Value	4.5		7.5	RAW FABRIC
COLOUR FASTNESS	Test Method	units	MIN	AVG	MAX	REMARKS
CROCKING Dry	AATCC 8	rating	3			RAW FABRIC
CROCKING Wet	AATCC 8	rating	1.5			RAW FABRIC
VISUAL	Test Method	units	MIN	AVG	MAX	REMARKS
Dp/100m2		dP		14	20	
Major Defects/100m		#defects			5	
Piece Length		Mt	15			
Roll Length		Mt	30			
#Piece / Roll		pcs			3	
Max SHADE(for 0<>5000 mt shipments)		Value			4	
Max SHADE(for 5000<>10000mt shipm		Value			6	
Max SHADE(for 10000< mt shipments)		Value			8	

Care Instructions	Certifications
Fabric:  Inside-out; Wash&Dry Separately	   
	