

Date:	07.03.2024		
Code:	DRS506208	Quality Control system:	4 Point System
Type:	Denim Dual-Fix	Weave:	3/1 Z
Fabric Name:	DUNCAN /M OCEAN	Finishing:	Pre Wash + H.S
Composition:	62CO + 30TEN + 6EME + 2LY	Color:	Ocean Blue /7.5
Shade Control:	Stone wash 45min		

Physical Properties		Actual	Unit	Tolerance		Standards	Remarks
Weight		8.75	oz/y²	±5%		ASTM D3776 (2013)	Unwashed
Weight Washed		9.75	oz/y²	±5%		ASTM D3776 (2013)	Washed AATCC 135-2004(3x60HL)
Total Average Width		150	cm	-		ASTM D3774 (2012)	Unwashed
		59.1	inch	-			
Minimum Cuttable Width		145	cm	-		ASTM D3774 (2012)	Unwashed
		57.1	inch	-			
Shrinkage Warp		2.5	%	min. 0	max. 4	AATCC 135 (2004)	Washed (3x60HL)
Shrinkage Weft		11	%	±2		AATCC 135 (2004)	Washed (3x60HL)
Movement		0	%	±3		AATCC 179 (2004)	Washed (3x60HL)
Tear Warp	ELMENDORF	6120	g	min. 3970		ASTM D1424 (2013)	Washed (3x60HL)
		13.5	lbf	min. 8.775			
Tear Weft	ELMENDORF	9070	g	min. 5890		ASTM D1424 (2013)	Washed (3x60HL)
		20	lbf	min. 13			
Tensile Strength Warp		68040	g	min. 44220		ASTM D5034 (2013)	Washed (3x60HL)
		150	lbf	min. 97.5			
Tensile Strength Weft		27210	g	min. 17680		ASTM D5034 (2013)	Washed (3x60HL)
		60	lbf	min. 39			
Stiffness		1.1	KGF	±0.2		ASTM D4032 (2012)	Unwashed
Elasticity		46	%	min. 42	max. 50	ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Growth		3	%			ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Abrasion Resistance	MARTINDALE		rub/s	-		ISO 12947-2 (1998)	Max 20.000 Rubs or 2 Thread Breaks
Seam Slippage			-			ISO 13936-2	Washed
Pilling Tendency	MARTINDALE		-			ISO 12945-2 (2000)	Washed
pH		6	-	min. 4.5	max. 7.5	ISO 3071: (2020)	
Crocking Dry(Rubbing)		3-4	-			ISO 105-X12 (2001)	Unwashed
Crocking Wet		1-2	-			ISO 105-X12 (2001)	Unwashed

Care Instructions

Wash	Iron	Chlorinate	Dry clean	Temporal Dry
				

Notes :

- The roll length is measured by calibrated inspection with machines tolerance ± 1% : ISO 3933:1976.
- Please inspect before cutting, no claims acceptable after cutting.
- Please note that heavy washing recipes (stone washes, heavy brushing-scraping, and use of bleach or similar chemicals) may cause problems, Therefore the customer should do the washing trials before bulk production.
- Please be informed that we cannot accept any claim after six Months from invoice issuing date.

