

Date:	19.06.2021		
Code:	FRS901112	Quality Control system:	4 Point System
Type:	Gabardine Dual-Fix Blended With "Ten + Mod"	Weave:	3/1 Z
Fabric Name:	FARAFRA GR DC /B SING	Finishing:	Singeing
Composition:	46CO-Organic + 36TEN + 9MOD + 7T400 + 2LY	Color:	Stay Black 9250
Shade Control:	un-washed		

Physical Properties		Actual	Unit	Tolerance		Standards	Remarks
Weight		350	g/m²	±5%		ASTM D3776 (2013)	Raw Fabric
Total Average Width		145	cm	-		ASTM D3774 (2012)	Raw Fabric
		57.1	inch	-			
Minimum Cuttable Width		140	cm	-		ASTM D3774 (2012)	Raw Fabric
		55.1	inch	-			
Shrinkage Warp		2.5	%	min. 0	max. 4	AATCC 135 (2004)	Washed (3x60HL)
Shrinkage Weft		8	%	±2		AATCC 135 (2004)	Washed (3x60HL)
Movement		0	%	±3		AATCC 179 (2004)	Washed (3x60HL)
Tear Warp	ELMENDORF	9070	g	min. 5890		ASTM D1424 (2013)	Raw Fabric
		20	lbf	min. 13			
Tear Weft	ELMENDORF	4000	g	min. 2600		ASTM D1424 (2013)	Raw Fabric
		8.82	lbf	min. 5.733			
Tensile Strength Warp		90260	g	min. 58660		ASTM D5034 (2013)	Raw Fabric
		199	lbf	min. 129.35			
Tensile Strength Weft		28440	g	min. 18480		ASTM D5034 (2013)	Raw Fabric
		62.7	lbf	min. 40.755			
Stiffness			KGF	±0.2		ASTM D4032 (2012)	Raw Fabric
Elasticity		30	%	min. 26	max. 34	ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Growth		5	%			ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Abrasion Resistance	MARTINDALE		rubs	-		ISO 12947-2 (1998)	Max 20.000 Rubs or 2 Thread Breaks
Seam Slippage			-			ISO 13936-2	Raw Fabric
Pilling Tendency	MARTINDALE		-			ISO 12945-2 (2000)	Raw Fabric
pH			-	min. 4.5	max. 7.5	ISO 3071 (2020)	

* For PFD fabric, some physical properties will be changed as following (washing at 90 temperature for 60 min).

Shrinkage Warp		Shrinkage Weft	
Elasticity		Growth	

Care Instructions

Wash	Iron	Chlorinate	Dry clean	Temporal Dry
				

Notes :

- The roll length is measured by calibrated inspection with machines tolerance ± 1% : ISO 3933:1976.
- Please inspect before cutting, no claims acceptable after cutting.
- Please note that heavy washing recipes (stone washes, heavy brushing-scrapping, and use of bleach or similar chemicals) may cause problems, Therefore the customer should do the washing trials before bulk production.
- Please be informed that we cannot accept any claim after six Months from invoice issuing date.
- Above physical values belong only for sample production, In bulk production values could be changed.

