

Date:		Status:	Under Development
Code:	DRS901029	Quality Control system:	4 Point System
Type:	Denim Dual-Fix Blended With "Ten + Mod" Over Dye	Weave:	3/1 Z
Fabric Name:	FARAFRA /M DC OCEAN O.D	Finishing:	O.D + H.S
Composition:	46CO-Organic + 36TEN + 9MOD + 7T400 + 2LY	Color:	Ocean Blue /7.5 * Black /0605
Shade Control:	Enzyme wash 30min		

Physical Properties		Actual	Unit	Tolerance		Standards	Remarks
Weight		10.75	oz/y ²	±5%		ASTM D3776 (2013)	Raw Fabric
Weight Washed		12.25	oz/y ²	±5%		ASTM D3776 (2013)	Washed AATCC 135-2004(3x60HL)
Total Average Width		150	cm	-		ASTM D3774 (2012)	Raw Fabric
		59.1	inch	-			
Minimum Cuttable Width		145	cm	-		ASTM D3774 (2012)	Raw Fabric
		57.1	inch	-			
Shrinkage Warp		2.5	%	min. 0	max. 4	AATCC 135 (2004)	Washed (3x60HL)
Shrinkage Weft		14	%	±2		AATCC 135 (2004)	Washed (3x60HL)
Movement		0	%	±3		AATCC 179 (2004)	Washed (3x60HL)
Tear Warp	ELMENDORF		g			ASTM D1424 (2013)	Washed (3x60HL)
			lbf				
Tear Weft	ELMENDORF		g			ASTM D1424 (2013)	Washed (3x60HL)
			lbf				
Tensile Strength Warp			g			ASTM D5034 (2013)	Washed (3x60HL)
			lbf				
Tensile Strength Weft			g			ASTM D5034 (2013)	Washed (3x60HL)
			lbf				
Stiffness			KGF	±0.2		ASTM D4032 (2012)	Raw Fabric
Elasticity		30	%	min. 26	max. 34	ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Growth		5	%			ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Abrasion Resistance	MARTINDALE		rubs	-		ISO 12947-2 (1998)	Max 20.000 Rubs or 2 Thread Breaks
Seam Slippage			-			ISO 13936-2	Washed
Pilling Tendency	MARTINDALE		-			ISO 12945-2 (2000)	Washed
pH			-	min. 4.5	max. 7.5	ISO 3071: (2020)	
Crocking Dry(Rubbing)			-			ISO 105-X12 (2001)	Raw Fabric
Crocking Wet			-			ISO 105-X12 (2001)	Raw Fabric

Care Instructions

Wash	Iron	Chlorinate	Dry clean	Temporal Dry
				

Notes :

- The roll length is measured by calibrated inspection with machines tolerance ± 1% : ISO 3933:1976.
- Please inspect before cutting, no claims acceptable after cutting.
- Please note that heavy washing recipes (stone washes, heavy brushing-scrapping, and use of bleach or similar chemicals) may cause problems, Therefore the customer should do the washing trials before bulk production.
- Please be informed that we cannot accept any claim after six Months from invoice issuing date.
- Above physical values belong only for sample production, In bulk production values could be changed.

