



OFFICE
Huzur Mahallesi Cendere Caddesi
No: 114 B Blok Kat:26 No:377
Skyland Sariyer Istanbul Turkey
PostCode. 34396
P. +90 212 465 80 99 | Ext
F. +90 212 465 82 32

MILL
Public Free Zone
Damietta, EGYPT
P: +20 (57) 229 23 30 Pbx
F: +20 (57) 229 2331 Pbx

FABRIC SPECIFICATION

ARTICLE NAME : KARDIYA TOPBLUE

PRD NO : 100348

SAMPLE NAME :

COLOR: : TOPBLUE

DATE:16/03/2022

CONSTRUCTION		QUALITY CONTROL	
WEAVE	3/1 RHT	QUALITY CONTROL SYSTEM	4 POINT SYSTEM
COMPOSITION	%82CO %1EL %12CLY %5EME	SHADE CONTROL SYSTEM	555
NOTE		SHADE CONTROL RECIPE	

PHYSICAL	Test Method	units	MIN	AVG	MAX	REMARKS
WEIGHT	ASTM D3776	gr/m2 ouns/yd2	306 9.00	322 9.50	338 9.97	RAW FABRIC
WEIGHT	ASTM D3776	gr/m2 ouns/yd2	362 10.68	381 11.25	400 11.80	1*90 HL
USABLE WIDTH		cm	140			RAW FABRIC
SHRINKAGE Warp	ISO 6330	%	-1		-4	1*90 HL
SHRINKAGE Weft	ISO 6330	%	-16		-20	1*90 HL
SKEW MOVEMENT	LS&CO Method 2	%	-3		3	1*90 HL
TEAR STRENGTH Warp	ASTM D1424	gr	4000			1*90 HL
TEAR STRENGTH Weft	ASTM D1424	gr	2800			1*90 HL
TENSILE STRENGTH Warp	ASTM D5034	kg	55			1*90 HL
TENSILE STRENGTH Weft	ASTM D5034	kg	35			1*90 HL
STIFFNESS	ASTM D4032	kg		N/A		RAW FABRIC
WARP ELONGATION	ASTM D3107	%		N/A		RAW FABRIC
WARP ELASTICITY	ASTM D3107	%		N/A		1*90 HL
WEFT ELASTICITY	ASTM D3107	%	42		50	1*90 HL
WARP GROWTH	ASTM D3107	%		N/A		1*90 HL
WEFT GROWTH	ASTM D3107	%			7	1*90 HL
SEAM SLIPPAGE (Warp x Weft)	ASTM D1683	kg		N/A		1*90 HL
pH	ISO 3071/Morapex	Value	4.5		7.5	RAW FABRIC
COLOUR FASTNESS	Test Method	units	MIN	AVG	MAX	REMARKS
CROCKING Dry	AATCC 8	rating	3			RAW FABRIC
CROCKING Wet	AATCC 8	rating	1.5			RAW FABRIC
VISUAL	Test Method	units	MIN	AVG	MAX	REMARKS
Dp/100m2		dP		14	20	
Major Defects/100m		#defects			5	
Piece Length		MT	15			
Roll Length		MT	30			
#Piece / Roll		pcs			3	
Max SHADE(for 0<>5000 mt shipments)		Value			4	
Max SHADE(for 5000<>10000mt shipm		Value			6	
Max SHADE(for 10000< mt shipments)		Value			8	

Care Instructions	Certifications
Fabric:	     
Garment:	