



DNM TEXTILE SPINNING, WEAVING and DYEING

OFFICE

Huzur Mahallesi Cendere Caddesi
No: 114 B Blok Kat:26 No:377
Skyland Sarıyer İstanbul Turkey
PostCode. 34396
P. +90 212 465 80 99 | Ext
F. +90 212 465 82 32
MILL
Public Free Zone Damietta Egypt
P. +20 57 229 23 30
F. +20 57 229 23 31

MILL

Public Free Zone
Damietta, EGYPT
P: +20 (57) 229 23 30 Pbx
F: +20 (57) 229 2331 Pbx

FABRIC SPECIFICATION

DATE : 16-02-2024

SHORT CODE : S12076L

ARTICLE NAME : KATARA BLACK

CONSTRUCTION

WEAVE	3/1 RHT	WARP NE	9.69
Note		WEFT NE	9.56
COLOR	NERO	WARP DENSITY(end/cm)	28.82
COMPOSITION	%91CO %1EL %4EME %4WS	WEFT DENSITY(fill/cm)	17.12

PHYSICAL	Test Method	units	MIN	AVG	MAX	REMARKS
WEIGHT	ASTM D3776	gm/m2 ouns/yd2	298 8.79	313 9.25	329 9.70	RAW FABRIC
WEIGHT	ASTM D3776	gm/m2 ouns/yd2	346 10.20	364 10.75	383 11.30	1*90 HL
USABLE WIDTH		Cm	155			RAW FABRIC
SHRINKAGE Warp	ISO 6330	%	-1		-4	1*90 HL
SHRINKAGE Weft	ISO 6330	%	-8		-12	1*90 HL
TEAR STRENGTH Warp	ASTM D1424	gm	4000			1*90 HL
TEAR STRENGTH Weft	ASTM D1424	gm	2800			1*90 HL
TENSILE STRENGTH Warp	ASTM D5034	kg	55			1*90 HL
TENSILE STRENGTH Weft	ASTM D5034	kg	35			1*90 HL
WARP ELASTICITY	ASTM D3107	%		N/A		1*90 HL
WEFT ELASTICITY	ASTM D3107	%	24		30	1*90 HL
WARP GROWTH	ASTM D3107	%		N/A		1*90 HL
WEFT GROWTH	ASTM D3107	%			7	1*90 HL
VISUAL	Test Method	units	MIN	AVG	MAX	REMARKS
Dp/100m2		dP		14	20	
Major Defects/100m		#defects			5	
Piece Length		Mt	15			
Roll Length		Mt	30			
#Piece / Roll		pcs			3	
Max SHADE(for 0<>5000 mt shipments)		Value			4	
Max SHADE(for 5000<>10000mt shipm)		Value			6	
Max SHADE(for 10000< mt shipments)		Value			8	

OFFICE

Huzur Mahallesi Cendere Caddesi
No: 114 B Blok Kat:26 No:377
Skyland Sarıyer İstanbul Turkey
PostCode. 34396
P. +90 212 465 80 99 | Ext
F. +90 212 465 82 32
MILL
Public Free Zone Damietta Egypt
P. +20 57 229 23 30
F. +20 57 229 23 31

MILL

Public Free Zone
Damietta, EGYPT
P: +20 (57) 229 23 30 Pbx
F: +20 (57) 229 2331 Pbx

FABRIC SPECIFICATION

DATE : 16-02-2024
SHORT CODE : S12076L
ARTICLE NAME : KATARA BLACK

CONSTRUCTION

WEAVE	3/1 RHT	WARP NE	9.69
Note		WEFT NE	9.56
COLOR	NERO	WARP DENSITY(end/cm)	28.82
COMPOSITION	%91CO %1EL %4EME %4WS	WEFT DENSITY(fill/cm)	17.12
QUALITY CONTROL			REMARKS
QUALITY CONTROL SYSTEM		4 POINT SYSTEM	
SHADE CONTROL SYSTEM		555	
SHADE CONTROL RECIPE		STONE WASH 35 MIN	
Care Instructions		Certifications	
Fabric:		      	
Garment:		     	
		110839	