

Date:	08-SEP-2022		
Code:	DRB504925	Quality Control System:	4 Point System
Type:	Denim Stretch Blended Over Dyed	Weave:	3/1 Z
Fabric Name:	MALONE BK/BK	Finishing:	O.D + H.S
Composition:	83CO + 15Recycled Post-Consumer PES + 2EA	Color:	Black * Black /0600
Shade Control:	Enzyme Wash 30min + Softener		

Physical Properties	Actual	Unit	Tolerance	Standards	Remarks
Weight Dry	9.75	oz/y2	±5%	ASTM D3776 (2013)	Raw Fabric
Weight Washed	11.75	oz/y2	±5%	ASTM D3776 (2013)	Washed AATCC 135-2004(3x60HL)
Total Average Width	150	cm	-	ASTM D3774 (2012)	Raw Fabric
	59.1	inch	-		
Minimum Cuttable Width	145	cm	-	ASTM D3774 (2012)	Raw Fabric
	57.1	inch	-		
Shrinkage Warp	2.5	%	min. 0 - max. 4	AATCC 135 (2004)	Washed (3x60HL)
Shrinkage Weft	14	%	±2	AATCC 135 (2004)	Washed (3x60HL)
Movement	0	%	±3	AATCC 179 (2004)	Washed (3x60HL)
Tear Warp - ELMENDROF	6570	g	min. 4270	ASTM D1424 (2013)	Washed (3x60HL)
	14.5	lbf	min. 9.425		
Tear Weft - ELMENDROF	6120	g	min. 3970	ASTM D1424 (2013)	Washed (3x60HL)
	13.5	lbf	min. 8.775		
Tensile Strength Warp	90720	g	min. 58960	ASTM D5034 (2013)	Washed (3x60HL)
	200	lbf	min. 130		
Tensile Strength Weft	38550	g	min. 25050	ASTM D5034 (2013)	Washed (3x60HL)
	85	lbf	min. 55.25		
Stiffness	1.6	KGF	±0.2	ASTM D4032 (2012)	Raw Fabric
Elasticity	45	%	min. 41 - max. 49	ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Growth	2	%	-	ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Abrasion Resistance - MARTINDALE		rubs	-	ISO 12947-2 (1998)	Max 20.000 Rubs or 2 Thread Breaks
Seam Slippage		-	-	ISO 13936-2	Washed
Pilling Tendency - MARTINDALE		-	-	ISO 12945-2 (2000)	Washed
PH	6	-	min. 4.5 - max. 7.5	ISO 3071 (2020)	
Crocking Dry(Rubbing)	'3-4'	-		ISO 105-X12 (2001)	Raw Fabric
Crocking Wet	'1-2'	-		ISO 105-X12 (2001)	Raw Fabric
Wash	Iron		Chlorinate	Dry clean	Temporal Dry
					

Notes:

- The roll length is measured by calibrated inspection with machines tolerance $\pm 1\%$: ISO 3933:1976.
- Please inspect before cutting, no claims acceptable after cutting.
- Please note that heavy washing recipes (stone washes, heavy brushing-scraping, and use of bleach or similar chemicals) may cause problems, Therefore the customer should do the washing trials before bulk production.
- Please be informed that we cannot accept any claim after six Months from invoice issuing date.
- Above physical values belong only for sample production, In bulk production values could be changed.

