

Date:	19-JUN-2022		
Code:	DRB504722	Quality Control System:	4 Point System
Type:	Denim Stretch Blended	Weave:	3/1 Z
Fabric Name:	MALONE OCEAN	Finishing:	Pre Wash + H.S
Composition:	83CO + 15Recycled Post-Consumer PES + 2EA	Color:	Ocean Blue /7.5
Shade Control:	Stone wash 45min		

Physical Properties	Actual	Unit	Tolerance	Standards	Remarks
Weight Dry	9.75	oz/y2	±5%	ASTM D3776 (2013)	Raw Fabric
Weight Washed	11.75	oz/y2	±5%	ASTM D3776 (2013)	Washed AATCC 135-2004(3x60HL)
Total Average Width	150	cm	-	ASTM D3774 (2012)	Raw Fabric
	59.1	inch	-		
Minimum Cuttable Width	145	cm	-	ASTM D3774 (2012)	Raw Fabric
	57.1	inch	-		
Shrinkage Warp	2.5	%	min. 0 - max. 4	AATCC 135 (2004)	Washed (3x60HL)
Shrinkage Weft	14	%	±2	AATCC 135 (2004)	Washed (3x60HL)
Movement	0	%	±3	AATCC 179 (2004)	Washed (3x60HL)
Tear Warp - ELMENDROF	6800	g	min. 4420	ASTM D1424 (2013)	Washed (3x60HL)
	15	lbf	min. 9.75		
Tear Weft - ELMENDROF	5890	g	min. 3820	ASTM D1424 (2013)	Washed (3x60HL)
	13	lbf	min. 8.45		
Tensile Strength Warp	83910	g	min. 54540	ASTM D5034 (2013)	Washed (3x60HL)
	185	lbf	min. 120.25		
Tensile Strength Weft	36280	g	min. 23580	ASTM D5034 (2013)	Washed (3x60HL)
	80	lbf	min. 52		
Stiffness	1.3	KGF	±0.2	ASTM D4032 (2012)	Raw Fabric
Elasticity	45	%	min. 41 - max. 49	ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Growth	2	%	-	ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Abrasion Resistance - MARTINDALE		rubs	-	ISO 12947-2 (1998)	Max 20.000 Rubs or 2 Thread Breaks
Seam Slippage		-	-	ISO 13936-2	Washed
Pilling Tendency - MARTINDALE		-	-	ISO 12945-2 (2000)	Washed
PH	6	-	min. 4.5 - max. 7.5	ISO 3071 (2020)	
Crocking Dry(Rubbing)	'3-4'	-		ISO 105-X12 (2001)	Raw Fabric
Crocking Wet	'1-2'	-		ISO 105-X12 (2001)	Raw Fabric
Wash	Iron	Chlorinate	Dry clean	Temporal Dry	
					

Notes:

- The roll length is measured by calibrated inspection with machines tolerance $\pm 1\%$: ISO 3933:1976.
- Please inspect before cutting, no claims acceptable after cutting.
- Please note that heavy washing recipes (stone washes, heavy brushing-scraping, and use of bleach or similar chemicals) may cause problems, Therefore the customer should do the washing trials before bulk production.
- Please be informed that we cannot accept any claim after six Months from invoice issuing date.
- Above physical values belong only for sample production, In bulk production values could be changed.

