

Date:	27.06.2022		
Code:	DRS504659	Quality Control system:	4 Point System
Type:	Denim Dual-Fix	Weave:	3/1 Z
Fabric Name:	REX 21120 /46 OCEAN	Finishing:	TM + H.S
Composition:	91CO + 6T400 + 3LY	Color:	Ocean Blue /7.5
Shade Control:	Stone wash 45min		

Physical Properties		Actual	Unit	Tolerance		Standards	Remarks
Weight		10	oz/y ²	±5%		ASTM D3776 (2013)	Raw Fabric
Weight Washed		10.5	oz/y ²	±5%		ASTM D3776 (2013)	Washed AATCC 135-2004(3x60HL)
Total Average Width		132	cm	-		ASTM D3774 (2012)	Raw Fabric
		52	inch	-			
Minimum Cuttable Width		127	cm	-		ASTM D3774 (2012)	Raw Fabric
		50	inch	-			
Shrinkage Warp		2.5	%	min. 0	max. 4	AATCC 135 (2004)	Washed (3x60HL)
Shrinkage Weft		5	%	±2		AATCC 135 (2004)	Washed (3x60HL)
Movement		0	%	±3		AATCC 179 (2004)	Washed (3x60HL)
Tear Warp	ELMENDORF	4980	g	min. 3230		ASTM D1424 (2013)	Washed (3x60HL)
		11	lbf	min. 7.15			
Tear Weft	ELMENDORF	3170	g	min. 2060		ASTM D1424 (2013)	Washed (3x60HL)
		7	lbf	min. 4.55			
Tensile Strength Warp		72570	g	min. 47170		ASTM D5034 (2013)	Washed (3x60HL)
		160	lbf	min. 104			
Tensile Strength Weft		31750	g	min. 20630		ASTM D5034 (2013)	Washed (3x60HL)
		70	lbf	min. 45.5			
Stiffness		1.7	KGF	±0.2		ASTM D4032 (2012)	Raw Fabric
Elasticity		45	%	min. 41	max. 49	ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Growth		3	%			ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Abrasion Resistance	MARTINDALE		rubs	-		ISO 12947-2 (1998)	Max 20.000 Rubs or 2 Thread Breaks
Seam Slippage			-			ISO 13936-2	Washed
Pilling Tendency	MARTINDALE		-			ISO 12945-2 (2000)	Washed
pH		6.5	-	min. 4.5	max. 7.5	ISO 3071: (2020)	
Crocking Dry(Rubbing)		3-4	-			ISO 105-X12 (2001)	Raw Fabric
Crocking Wet		1-2	-			ISO 105-X12 (2001)	Raw Fabric

Care Instructions

Wash	Iron	Chlorinate	Dry clean	Temporal Dry
				

Notes :

- The roll length is measured by calibrated inspection with machines tolerance ± 1% : ISO 3933:1976.
- Please inspect before cutting, no claims acceptable after cutting.
- Please note that heavy washing recipes (stone washes, heavy brushing-scrapping, and use of bleach or similar chemicals) may cause problems, Therefore the customer should do the washing trials before bulk production.
- Please be informed that we cannot accept any claim after six Months from invoice issuing date.

