

|                       |                        |                                |                   |
|-----------------------|------------------------|--------------------------------|-------------------|
| <b>Date:</b>          | 01.02.2023             | <b>Status:</b>                 | Under Development |
| <b>Code:</b>          | DRS05040               | <b>Quality Control system:</b> | 4 Point System    |
| <b>Type:</b>          | Denim Stretch          | <b>Weave:</b>                  | 3/1 Z             |
| <b>Fabric Name:</b>   | <b>SANMAR 35 BLACK</b> | <b>Finishing:</b>              | CK + H.S          |
| <b>Composition:</b>   | 97.5CO + 2.5EA         | <b>Color:</b>                  | Black             |
| <b>Shade Control:</b> | Stone wash 45min       |                                |                   |

| Physical Properties    |            | Actual | Unit              | Tolerance  |          | Standards                  | Remarks                            |
|------------------------|------------|--------|-------------------|------------|----------|----------------------------|------------------------------------|
| Weight                 |            | 8      | oz/y <sup>2</sup> | ±5%        |          | ASTM D3776 (2013)          | Raw Fabric                         |
| Weight Washed          |            | 8.75   | oz/y <sup>2</sup> | ±5%        |          | ASTM D3776 (2013)          | Washed AATCC 135-2004(3x60HL)      |
| Total Average Width    |            | 160    | cm                | -          |          | ASTM D3774 (2012)          | Raw Fabric                         |
|                        |            | 63     | inch              | -          |          |                            |                                    |
| Minimum Cuttable Width |            | 155    | cm                | -          |          | ASTM D3774 (2012)          | Raw Fabric                         |
|                        |            | 61     | inch              | -          |          |                            |                                    |
| Shrinkage Warp         |            | 2.5    | %                 | min. 0     | max. 4   | AATCC 135 (2004)           | Washed (3x60HL)                    |
| Shrinkage Weft         |            | 7      | %                 | ±2         |          | AATCC 135 (2004)           | Washed (3x60HL)                    |
| Movement               |            | 0      | %                 | ±3         |          | AATCC 179 (2004)           | Washed (3x60HL)                    |
| Tear Warp              | ELMENDORF  | 5890   | g                 | min. 3820  |          | ASTM D1424 (2013)          | Washed (3x60HL)                    |
|                        |            | 13     | lbf               | min. 8.45  |          |                            |                                    |
| Tear Weft              | ELMENDORF  | 2720   | g                 | min. 1760  |          | ASTM D1424 (2013)          | Washed (3x60HL)                    |
|                        |            | 6      | lbf               | min. 3.9   |          |                            |                                    |
| Tensile Strength Warp  |            | 77110  | g                 | min. 50120 |          | ASTM D5034 (2013)          | Washed (3x60HL)                    |
|                        |            | 170    | lbf               | min. 110.5 |          |                            |                                    |
| Tensile Strength Weft  |            | 22680  | g                 | min. 14740 |          | ASTM D5034 (2013)          | Washed (3x60HL)                    |
|                        |            | 50     | lbf               | min. 32.5  |          |                            |                                    |
| Stiffness              |            | 0.7    | KGF               | ±0.2       |          | ASTM D4032 (2012)          | Raw Fabric                         |
| Elasticity             |            | 35     | %                 | min. 31    | max. 39  | ASTM D3107 (4lb)- Modified | Washed AATCC 135-2004(3x60HL)      |
| Growth                 |            | 5      | %                 |            |          | ASTM D3107 (4lb)- Modified | Washed AATCC 135-2004(3x60HL)      |
| Abrasion Resistance    | MARTINDALE |        | rubs              | -          |          | ISO 12947-2 (1998)         | Max 20.000 Rubs or 2 Thread Breaks |
| Seam Slippage          |            |        | -                 |            |          | ISO 13936-2                | Washed                             |
| Pilling Tendency       | MARTINDALE |        | -                 |            |          | ISO 12945-2 (2000)         | Washed                             |
| pH                     |            | 6      | -                 | min. 4.5   | max. 7.5 | ISO 3071: (2020)           |                                    |
| Crocking Dry(Rubbing)  |            | 4      | -                 |            |          | ISO 105-X12 (2001)         | Raw Fabric                         |
| Crocking Wet           |            | 2      | -                 |            |          | ISO 105-X12 (2001)         | Raw Fabric                         |

#### Care Instructions

| Wash                                                                                | Iron                                                                                | Chlorinate                                                                          | Dry clean                                                                             | Temporal Dry                                                                          |
|-------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|
|  |  |  |  |  |

#### Notes :

- The roll length is measured by calibrated inspection with machines tolerance ± 1% : ISO 3933:1976.
- Please inspect before cutting, no claims acceptable after cutting.
- Please note that heavy washing recipes (stone washes, heavy brushing-scrapping, and use of bleach or similar chemicals) may cause problems, Therefore the customer should do the washing trials before bulk production.
- Please be informed that we cannot accept any claim after six Months from invoice issuing date.
- Above physical values belong only for sample production, In bulk production values could be changed.

