



OFFICE
Huzur Mahallesi Cendere Caddesi
No: 114 B Blok Kat:26 No:377
Skyland Sariyer Istanbul Turkey
PostCode. 34396
P. +90 212 465 80 99 | Ext
F. +90 212 465 82 32

MILL
Public Free Zone
Damietta, EGYPT
P: +20 (57) 229 23 30 Pbx
F: +20 (57) 229 2331 Pbx

TEMPORARY FABRIC SPECIFICATION

ARTICLE NAME : C1568-A STR G1

PDR Name : 101975

DATE : 12.3.2023

SHORT CODE : TTR5376G

CONSTRUCTION			QUALITY CONTROL			
WEAVE	2/1 RHT		QUALITY CONTROL SYSTEM		4 POINT SYSTEM	
COMPOSITION	%75CO %3EL %17PES %5EME		SHADE CONTROL SYSTEM		555	
Note			SHADE CONTROL RECIPE		STONE WASH 35 MIN	
PHYSICAL	Test Method	units	MIN	AVG	MAX	REMARKS
WEIGHT	ASTM D3776	gr/m2 ouns/yd2	234 6.90	245 7.25	258 7.61	RAW FABRIC
WEIGHT	ASTM D3776	gr/m2 ouns/yd2	258 7.61	271 8.00	285 8.40	1*90 HL
USABLE WIDTH		cm	137			RAW FABRIC
SHRINKAGE Warp	ISO 6330	%	-1		-4	1*90 HL
SHRINKAGE Weft	ISO 6330	%	-7		-11	1*90 HL
SKEW MOVEMENT	LS&CO Method 2	%	-3		3	1*90 HL
TEAR STRENGTH Warp	ASTM D1424	gr	3100			1*90 HL
TEAR STRENGTH Weft	ASTM D1424	gr	2100			1*90 HL
TENSILE STRENGTH Warp	ASTM D5034	kg	40			1*90 HL
TENSILE STRENGTH Weft	ASTM D5034	kg	30			1*90 HL
STIFFNESS	ASTM D4032	kg		N/A		RAW FABRIC
WARP ELONGATION	ASTM D3107	%		N/A		RAW FABRIC
WARP ELASTICITY	ASTM D3107	%		N/A		1*90 HL
WEFT ELASTICITY	ASTM D3107	%	20		26	1*90 HL
WARP GROWTH	ASTM D3107	%		N/A		1*90 HL
WEFT GROWTH	ASTM D3107	%			6	1*90 HL
SEAM SLIPPAGE (Warp x Weft)	ASTM D1683	kg		N/A		1*90 HL
pH	ISO 3071/Morapex	Value	4.5		7.5	RAW FABRIC
COLOUR FASTNESS	Test Method	units	MIN	AVG	MAX	REMARKS
CROCKING Dry	AATCC 8	rating	3			RAW FABRIC
CROCKING Wet	AATCC 8	rating	1.5			RAW FABRIC
VISUAL	Test Method	units	MIN	AVG	MAX	REMARKS
Dp/100m2		dP		14	20	
Major Defects/100m		#defects			5	
Piece Length		MT	15			
Roll Length		MT	30			
#Piece / Roll		pcs			3	
Max SHADE(for 0<>5000 mt shipments)		Value			4	
Max SHADE(for 5000<>10000mt shipm		Value			6	
Max SHADE(for 10000< mt shipments)		Value			8	
Care Instructions		Certifications				
Fabric:		   				
Garment:  Inside-out; Wash&Dry Separately						