

			Fabric Specification			
Date:	15-FEB-2022			Status:	Under Development	
Code:	DRS504188			Quality Control System:	4 Point System	
TYPE:	Denim Dual-Force			Weave:	3/1 Z	
Fabric Name:	ULTRA JET 85 OCEAN			Finishing:	Pre Shrunk	
Composition:	92CO + 6T400 + 2LY			Color:	Ocean Blue /7.5	
Shade Control:	Stone wash 45min					
Physical Properties		Actual	Unit	Tolerance	Standards	Remarks
Weight Dry		9.25	oz/y2	±5%	ASTM D3776 (2013)	Raw Fabric
Weight Washed		11	oz/y2	±5%	ASTM D3776 (2013)	Washed AATCC 135-2004(3x60HL)
Total Average Width		145	cm	-	ASTM D3774 (2012)	Raw Fabric
		57.1	inch	-		
Minimum Cuttable Width		140	cm	-	ASTM D3774 (2012)	Raw Fabric
		55.1	inch	-		
Shrinkage Warp		2.5	%	min. 0 - max. 4	AATCC 135 (2004)	Washed (3x60HL)
Shrinkage Weft		16	%	±2	AATCC 135 (2004)	Washed (3x60HL)
Movement		0	%	±3	AATCC 179 (2004)	Washed (3x60HL)
Tear Warp - ELMENDROF		6800	g	min. 4420	ASTM D1424 (2013)	Washed (3x60HL)
		15	lbf	min. 9.75		
Tear Weft - ELMENDROF		4300	g	min. 2790	ASTM D1424 (2013)	Washed (3x60HL)
		9.5	lbf	min. 6.175		
Tensil Strength Warp		70300	g	min. 45690	ASTM D5034 (2013)	Washed (3x60HL)
		155	lbf	min. 100.75		
Tensil Strength Weft		24940	g	min. 16210	ASTM D5034 (2013)	Washed (3x60HL)
		55	lbf	min. 35.75		
Stiffness		1.1	KGF	±0.2	ASTM D4032 (2012)	Raw Fabric
Elasticity		62	%	min. 57 - max. 67	ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Growth		3	%	-	ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Abrasion Resistance - MARTINDALE			rubs	-	ISO 12947-2 (1998)	Max 20.000 Rubs or 2 Thread Breaks
Seam Slippage			-	-	ISO 13936-2	Washed
Pilling Tendency - MARTINDALE			-	-	ISO 12945-2 (2000)	Washed
PH		6.5	-	min. 4.5 - max. 7.5	ISO 3071 (2020)	
Crocking Dry(Rubbing)		'3-4'	-		ISO 105-X12 (2001)	Raw Fabric
Crocking Wet		'1-2'	-		ISO 105-X12 (2001)	Raw Fabric
Wash	Iron		Chlorinate		Dry clean	Temporal Dry
						

Notes:

- The roll length is measured by calibrated inspection with machines tolerance ± 1% : ISO 3933:1976.
- Please inspect before cutting, no claims acceptable after cutting.
- Please note that heavy washing recipes (stone washes, heavy brushing-scrapping, and use of bleach or similar chemicals) may cause problems, Therefore the customer should do the washing trials before bulk production.
- Please be informed that we cannot accept any claim after six Months from invoice issuing date.
- Above physical values belong only for sample production, In bulk production values could be changed.

