

Date:	21.10.2024	Status:	Under Development
Code:	DRS505638	Quality Control system:	4 Point System
Type:	Denim Dual-Fix Printed	Weave:	3/1 Z
Fabric Name:	ULTRA JET 86 BLACK PD	Finishing:	Pre Shrunk + Printing
Composition:	92CO + 6EME + 2LY	Color:	Black * A31101G
Shade Control:	Enzyme wash 30min	Color Note:	

Physical Properties		Actual	Unit	Tolerance		Standards	Remarks
Weight		9.25	oz/y²	±5%		ASTM D3776 (2013)	Unwashed
Weight Washed		9.75	oz/y²	±5%		ASTM D3776 (2013)	Washed AATCC 135-2004(3x60HL)
Total Average Width		145	cm	-		ASTM D3774 (2012)	Unwashed
		57.1	inch	-			
Minimum Cuttable Width		140	cm	-		ASTM D3774 (2012)	Unwashed
		55.1	inch	-			
Shrinkage Warp		2.5	%	min. 0	max. 4	AATCC 135 (2004)	Washed (3x60HL)
Shrinkage Weft		11	%	±2		AATCC 135 (2004)	Washed (3x60HL)
Movement		0	%	±3		AATCC 179 (2004)	Washed (3x60HL)
Tear Warp	ELMENDORF	6350	g	min. 4120		ASTM D1424 (2013)	Washed (3x60HL)
		14	lbf	min. 9.1			
Tear Weft	ELMENDORF	3620	g	min. 2350		ASTM D1424 (2013)	Washed (3x60HL)
		8	lbf	min. 5.2			
Tensile Strength Warp		70300	g	min. 45690		ASTM D5034 (2013)	Washed (3x60HL)
		155	lbf	min. 100.75			
Tensile Strength Weft		22680	g	min. 14740		ASTM D5034 (2013)	Washed (3x60HL)
		50	lbf	min. 32.5			
Stiffness		0.8	KGF	±0.2		ASTM D4032 (2012)	Unwashed
Elasticity		46	%	min. 42	max. 50	ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Growth		3	%			ASTM D3107 (4lb)- Modified	Washed AATCC 135-2004(3x60HL)
Abrasion Resistance	MARTINDALE		rub/s	-		ISO 12947-2 (1998)	Max 20.000 Rubs or 2 Thread Breaks
Seam Slippage			-			ISO 13936-2	Washed
Pilling Tendency	MARTINDALE		-			ISO 12945-2 (2000)	Washed
pH		6	-	min. 4.5	max. 7.5	ISO 3071: (2020)	
Crocking Dry(Rubbing)			-			ISO 105-X12 (2001)	Unwashed
Crocking Wet			-			ISO 105-X12 (2001)	Unwashed

Care Instructions

Wash	Iron	Chlorinate	Dry clean	Temporal Dry
				

Notes :

- The roll length is measured by calibrated inspection with machines tolerance ± 1% : ISO 3933:1976.
- Please inspect before cutting, no claims acceptable after cutting.
- Please note that heavy washing recipes (stone washes, heavy brushing-scraping, and use of bleach or similar chemicals) may cause problems, Therefore the customer should do the washing trials before bulk production.
- Please be informed that we cannot accept any claim after six Months from invoice issuing date.
- Above physical values belong only for sample production, In bulk production values could be changed.

