↑ AETD Bronze StrataS23   ↓

Visual Hue Request: [   ]

| New Std | Retrieve Std | Store Std | List Std |

Instrument Setup:%R LAV SCI UV Cal

Date: 27-Apr-21   Time: 08:00:54

Batch Name   1   of   1

↑ 'GFS 56977 SME2300096 AETD BRONZE   ↓

| New Bat | Retrieve Bat | Store Bat | List Bat |

Instrument Setup: %R LAV SCI UV Cal

Date: 10-Jul-23   Time: 13:29:03

Delta [D65 / 10] [F11 / 10]

| Single/All | Zoom In | Zoom Out | CMC Plot | Print Form |

DataColor TOOLS 2.8.1   **S/N NO. 8823242**

Standard %R

400-450nm	6.69	4.95	4.07	3.55	3.35	3.34
460-510nm	3.57	4.05	5.40	7.11	8.22	8.76
520-570nm	9.47	10.38	11.15	11.83	12.72	13.75
580-630nm	14.91	16.14	17.83	19.56	19.69	19.34
640-690nm	19.39	21.30	24.71	36.88	52.38	60.53
700nm	71.01					

CMC DE Pass/Fail Tolerance: 0.80

l:c Ratio: (2.00   1.00)

Batch Name	Ill/Obs	DL*	Da*	Db*	DL*/lSL	DC*/cSC	DH*/SH	CMC DE	M.I.	P/F			Color Comments
60017206 23040747GFS 56977 SME2300096 AETD BRONZE	D65 10 Deg	0.10	0.76	0.44	0.05	0.32	-0.58	**0.66**		Warn	too light	too bright	too red
60017206 23040747GFS 56977 SME2300096 AETD BRONZE	F11 10 Deg	0.42	-0.84	0.90	0.21	0.29	0.98	**1.04**	1.71	Fail	too light	too bright	too yellow