



**Methacrylate Adhesive** 

**ForzaBOND® M-R478** is a 2-part methacrylate adhesive designed to bond a wide range of substrates.

## **Benefits**

- Excellent bond strength
- · Impact and weather resistant
- 1:1 ratio easy mixing or dispensing
- · Minimal surface preparation required
- Forms tough, high-strength, high-impact resistant bonds
- Resists most common industrial cleaners, fuels, lubricants, and environmental conditions
- Retains bond in strength in boiling water, salt water, salt fog, kerosene, gasoline, diesel fuel, antifreeze, hydraulic fluid, and cutting oils.

## **Product Application**

- When using cartridges, ensure flow from both sides of cartridge dispenser; attach static mixer and gun out material.
- After adhesive is mixed apply it to one surface to be bonded then mate the second surface.
- Surfaces should be clean and dry and in most cases no abrasion or solvent wipe is necessary.
- You have only 3-4 minutes to put parts together. Hold parts in position while curing (pressure clamping is not required).
- At room temperature handling strength is achieved at 7-10 minutes and in full cure in 2-3 hours.

## **Applications**

**ForzaBOND**° **M-R478** bonds engineered thermoplastics, thermosets, composites, rubbers, and metals without the need for surface preparation, primers, or chemical wipes. Ideally suited for structural applications.

## **Technical Data**

Appearance:	White
Cure Properties:	5 mins in mixer nizzle, allow 30 mins to handle
Elongation:	40%
Full Cure:	2-3 hours
Handling Strength:	5-6 minutes
Sored Hardness:	70-75
Steel-Steel:	4,200 psi
Aluminum - Aluminum:	3,400 psi
Viscosity:	200,000 CPS
Sizes	
50ml Cartridge	5 Gallon

52 Gallon Drum

CREATING INDUSTRIAL ADHESIVE, TAPE, AND SEALANT SOLUTIONS THAT OUTPERFORM

400ml Cartridge

