

Permittivity @ 1MHz (Laminate and prepreg as laminated)	4,2-4,6	5,4	4,6-4,9	5,4		2.5.5.2 2.5.5.3 2.5.5.9
Loss Tangent @ 1MHz (Laminate and prepreg as laminated)	0,015-0,02	0,035	0,015-0,02	0,035		2.5.5.2 2-5.5.3 2.5.5.9