

Vibrating Sample Magnetometry

Theoretical principle

Faraday's law of induction

$$V(t) = -\frac{d\phi_B}{dt} \quad (1)$$

$$\phi_B = \iint_S \vec{B}(\vec{r}, t) \cdot d\vec{A} = BS \quad (2)$$

$$\Rightarrow V(z, t) = -NS \frac{dB}{dz} \frac{dz}{dt} \quad (3)$$

Magnetization


- **Paramagnetism:** Magnetic moment of unpaired electrons
- **Diamagnetism:** Lorentz force on electrons in orbitals


Theoretical principle

Induction on one pickup coil


$$\begin{aligned} V(z) = & -N A S I \mu_0 \frac{f \pi}{\sqrt{2}} \left[\ln \left(r_2 + \sqrt{r_2^2 + (z-L)^2} \right) - \ln \left(r_1 + \sqrt{r_1^2 + (z-L)^2} \right) + \right. \\ & (z-L)^2 \left(\frac{1}{r_2 \sqrt{r_2^2 + (z-L)^2} + r_2^2 + (z-L)^2} - \frac{1}{r_1 \sqrt{r_1^2 + (z-L)^2} + r_1^2 + (z-L)^2} \right) + \\ & \ln \left(r_1 + \sqrt{r_1^2 + z^2} \right) - \ln \left(r_2 + \sqrt{r_2^2 + z^2} \right) + \\ & \left. z^2 \left(\frac{1}{r_1 \sqrt{r_1^2 + z^2} + r_1^2 + z^2} - \frac{1}{r_2 \sqrt{r_2^2 + z^2} + r_2^2 + z^2} \right) \right] \end{aligned} \quad (4)$$


One pickup coil, permanent magnet: 30.9 mg







All 4 pickup coils, Nickel: 42.5 mg at 2 T (Room Temperature)









Nickel: 42.5 mg (**Room Temperature**)

$$(58.57 \pm 0.03) \text{ emu/g} \implies (2.489 \pm 0.002) \text{ emu} \implies c = (29.34 \pm 0.06) \text{ emu}$$

Average of absolute value in
shaded area: 0.084839 ± 0.000153




$\text{CuSO}_4 \cdot 5 \text{H}_2\text{O}$: 143 mg (Room Temperature)



$\text{CuSO}_4 \cdot 5 \text{H}_2\text{O}$: 143 mg (4 K)

$$c = (29.34 \pm 0.06) \text{ emu} \implies (3.67 \pm 0.04) \text{ emu} \implies (25.7 \pm 0.3) \text{ emu/g}$$


Average of absolute value in
shaded area: 0.125318 ± 0.001352



Sanity Check


- Paramagnetic Cu²⁺ ions: Spin 1/2
- $2\sqrt{s(s+1)} = \sqrt{3} \mu_B$
- CuSO₄·5H₂O: 249.684 u
- $\implies 39 \text{ emu/g}$
- Diamagnetic contributions of H₂O and SO₄²⁻

KEr(MoO₄)₂: 6.2 mg




$\text{Ni}_{38}\text{Mn}_{49}\text{Sn}_9\text{Fe}_4$

Martensite (strained body-centered tetragonal), Austenite (face-centered cubic) phase transition.



$\text{Ni}_{37}\text{Mn}_{49}\text{Sn}_9\text{Fe}_5$

Martensite (strained body-centered tetragonal), Austenite (face-centered cubic) phase transition.



More info:

github.com/AndrewAmmerlaan/HFML-VSM_CoilProfilePlotter

Acknowledgements:

Thanks to Prof. dr. Uli Zeitler, Hung van Luong, dr. Dmytro Kamenskyi, Bence Bernáth and all the other staff and students at HFML. Also thanks to dr. Patricia Lázpita from the University of Basque Country and Anabel Pérez Checa from BCMaterials.

