valspar
if it matters, we're on it.®

Technical Data

1101 South 3rd Street
Minneapolis, MN 55415
612-851-4374

Date: May 17, 2018

Product # PFY90001

Product Description: YELLOW EPOXY TANK COATING

Specifications			
Physical Properties:			
Chemical Type	EPOXY		
Specific Gravity	1.43 ± 0.05		
Theoretical Coverage	134.81 SQ FT/LB @ 1 MIL		
Other Information			
Film Properties	**Method**		
Recommended Film Thickness		5 - 7 MIL	
Flexibility (Conical Mandrel)	ASTM D-522	PASS	
Adhesion	ASTM D-3359	PASS	
Gloss (60 degrees)	ASTM D-523	90 Minimum GU	
Cure Cycle	10 MIN. AT 400F		
Appearance	SMOOTH		
Application	ELECTROSTATIC SPRAY		
Pretreatment:	All testing was performed on clean panels with appropriate pretreatment. Proper pretreatment will enhance performance of this product.		
Substrate:	IRON PHOSPATE CHEMCIAL WASH		
Maximum Field Use Dry Film Thickness			
Number of Coats			
Recoat/Cure Time			
Maximum Thinner			
End Use			

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Valspar assumes no obligation or liability for use of this information**. UNLESS VALSPAR AGREES OTHERWISE IN WRITING, VALSPAR MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. VALSPAR WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. The information in this sheet, as well as the products referenced herein, shall be considered "Confidential Information". Wet samples and uncured samples of these products shall be maintained as confidential and shall not be disclosed to any third party without the prior written permission of Valspar.