

Coating Report

Main Coating

Main Coating Die Diameter (μm): 150.0

Main Entry Die Diameter (μm): 160.0

Main Density (g/cm^3): 1.05

Main Coating: Coat A

Main Coating Temp ($^{\circ}\text{C}$): 44.0

Main Viscosity ($\text{mPa}\cdot\text{s}$): 1.099

Main Estimated Thickness (μm): 151.02

Secondary Coating

Secondary Coating Die Diameter (μm): 190.0

Secondary Entry Die Diameter (μm): 200.0

Secondary Density (g/cm^3): 1.12

Secondary Coating: Coat B

Secondary Coating Temp ($^{\circ}\text{C}$): 44.0

Secondary Viscosity ($\text{mPa}\cdot\text{s}$): 1.398

Secondary Estimated Thickness (μm): 196.43