

US007984788B2

US 7,984,788 B2

Jul. 26, 2011

(12) United States Patent Seo

Date of Patent:

(54) LAMINATED ACOUSTIC ABSORPTION SHEET WITH FLAME RETARDANT

	(75)	Inventor	Duckcheol Seo, Cheo	non of (VD)
- 1	10	mventor.	Duckeneor Seo. Cheo	Hall-SI (N.K.)

- (73) Assignee: Huneco Co., Ltd., Pyeongtaek-si (KR)
- (*) Notice: Subject to any disclaimer, the term of this

patent is extended or adjusted under 35

U.S.C. 154(b) by 0 days.

- (21) Appl. No.: 12/516,707
- (22) PCT Filed: Nov. 27, 2007
- (86) PCT No.: PCT/KR2007/006039

§ 371 (c)(1),

(2), (4) Date: **Dec. 17, 2009**

(87) PCT Pub. No.: WO2008/066314

PCT Pub. Date: Jun. 5, 2008

(65) Prior Publication Data

US 2010/0108439 A1 May 6, 2010

(30) Foreign Application Priority Data

Nov. 29, 2006 (KR) 10-2006-0119379

(51)	Int. Cl.	
	E04B 1/84	(2006.01)
	E04B 1/82	(2006.01)
	E04B 1/88	(2006.01)
	B32B 7/08	(2006.01)
	E04B 1/74	(2006.01)
	B32B 7/00	(2006.01)

- (52) U.S. Cl. 181/294; 181/290; 181/286; 156/93

See application file for complete search history.

(56) References Cited

(10) **Patent No.:**

U.S. PATENT DOCUMENTS

			3.710 1
4,088,620	A *	5/1978	Nihongi et al 524/503
4,726,987	A *	2/1988	Trask et al 442/373
4,892,769	A *	1/1990	Perdelwitz et al 428/68
5,225,140		7/1993	Hayashikoshi et al 264/571
6,042,765	A *	3/2000	Sugahara et al 264/46.1
6,383,623	B1 *	5/2002	Erb, Jr 428/299.7
6,905,987	B2 *	6/2005	Noda et al 442/364
7,479,313	B2 *	1/2009	Chang et al 428/31
7,491,770	B2 *	2/2009	Autran et al 525/191
7,694,779	B2 *	4/2010	Takayasu et al 181/294
2003/0134556	A1*	7/2003	Christie et al 442/327
2005/0212166	A1*	9/2005	Seo et al 264/147
2007/0190876	A1*	8/2007	Ogawa et al 442/136
2009/0258559	A1*	10/2009	Anantharamaiah et al 442/334

FOREIGN PATENT DOCUMENTS

JP	11180224 A	*	7/1999
KR	2004060090 A	*	7/2004
KR	2005027598 A	*	3/2005
KR	2006032571 A	*	4/2006

^{*} cited by examiner

Primary Examiner — Edgardo San Martin (74) Attorney, Agent, or Firm — Rothwell, Figg, Ernst & Manbeck, P.C.

(57) ABSTRACT

The present invention relates to a light laminated acoustic absorption sheet. The light laminated acoustic absorption sheet with flame retardant is characterized in that one or more thermoplastic fibers (a) having a low melting point and selected from polyethylene, polypropylene, polyvinyl chloride, polyester, polyethylene-polyester copolymers, and one or more polyester interlaced-textured yarns or thermoplastic hollow fibers (b) having a higher melting point than the thermoplastic fiber (a) and selected from polyester, polyethylene, nylon, hot-meltable fluororesin are mixed and opened so as to prepare a mat, and two or more sheets of mats are laminated by using an apparatus of manufacturing a stampable sheet so as to manufacture the laminated sheet, and then the laminated sheet is impregnated with flame retardant liquid.

6 Claims, No Drawings