

United States Patent [19]

Moteki et al.

[11] Patent Number: 4,761,451

[45] Date of Patent: Aug. 2, 1988

[54] ACOUSTIC VIBRATION SHEET AND
POLYPROPYLENE COMPOSITION FOR
THE SAME

[75] Inventors: Tsutomu Moteki, Chibaken; Kunihiro
Yamaguchi; Hisao Iizuka, both of
Ichiharashi, all of Japan

[73] Assignee: Chisso Corporation, Osaka, Japan

[21] Appl. No.: 13,882

[22] Filed: Feb. 12, 1987

[30] Foreign Application Priority Data

Mar. 5, 1986 [JP] Japan 61-47930

[51] Int. Cl.⁴ C08K 3/04; C08K 3/34;
C08L 9/00; C08L 53/02

[52] U.S. Cl. 524/505; 524/13;
524/449; 524/451; 524/496; 525/98

[58] Field of Search 525/88, 98; 524/505

[56] References Cited

U.S. PATENT DOCUMENTS

4,464,439 8/1984 Castelein 525/98
4,499,238 2/1985 Iwata et al. 525/98
4,582,871 4/1986 Noro et al. 524/505

4,604,421 8/1986 Mitsuno et al. 524/505

FOREIGN PATENT DOCUMENTS

0187442 11/1983 Japan 525/98
0022948 2/1984 Japan 525/98
0149939 8/1984 Japan 525/98
1095056 5/1986 Japan 525/98

Primary Examiner—Herbert J. Lilling

Attorney, Agent, or Firm—Leydig, Voit & Mayer

[57] ABSTRACT

A polypropylene based composition for an acoustic vibration sheet having superior acoustic adhesion and high-impact properties to those of conventional products, and an acoustic vibration sheet prepared from the composition are provided; the composition is obtained by blending 100 parts by weight of a polypropylene having a crystallinity of 0.94 or more and a Q value of 10 or more with 1 to 15 parts by weight of a thermoplastic styrene block copolymer rubber, and if necessary, further blending 10 to 40 parts by weight of a filler with the above-mentioned two components.

4 Claims, No Drawings