

Durability of structures based on bio-sourced materials against three-dimensional crack problems

EL KABIR Soliman¹,

MOUTOU PITTI Rostand²,

DUBOIS Frédéric³,

LAPUSTA Yuri⁴,

RECHO Naman⁵,

¹ University of Limoges, Civil Engineering Center, GC2D, 19300 Egletons, France + soliman.el-kabir@unilim.fr

² Université Clermont Auvergne, CNRS, Institut Pascal, F-63000 Clermont-Ferrand, France
& CNAREST, IRT, BP 14070, Libreville, Gabon + rostand.moutou_pittil@uca.fr

³ University of Limoges, Civil Engineering Center, GC2D, 19300 Egletons, France + frederic.dubois@unilim.fr

⁴ SIGMA, Institut Pascal, 63171 Aubière, France + yuri.lapusta@sigma-clermont.fr

⁵ Université Clermont Auvergne, Institut Pascal, BP 10448, 63000 Clermont-Ferrand, France & EPF Engineering school,
& Sceaux, France + naman.recho@moniut.univ-bpclermont.fr

Résumé :

La durabilité des structures à base de matériaux biosourcés est confrontée à des problèmes de fissurations sous chargements mécaniques complexes associées à des variations climatiques sévères. L'objectif principal de ce travail est de présenter une nouvelle modélisation mathématique pour les problèmes de fissurations tridimensionnelle sous chargement en mode mixte. Le modèle repose sur nouvelle intégrale, intitulée M_{θ}^{3D} , dont l'implémentation dans un logiciel par élément finis permet d'obtenir le taux de restitution d'énergie ou la ténacité associée. En prenant le matériaux bois pour exemple, les résultats montrent comment évolue la résistance à la fissuration en fonction de différents taux de mixité.

1. Introduction

The complex mechanical loading and high climatic variations on structures implies having a better understanding of their fracture mechanical behavior. It is necessary to consider three-dimensional case in the study of reel crack growth problem. For it the most common approach is the determination of the energy release rate by energetic approach. Civil engineering and mechanical structures are usually submitted to mixed mode loading. As a consequence, a mixed mode crack growth process occurs.

This fact appears again as an important key in the case of three-dimensional medium. 2D idealization case can be applicable to a variety of engineering problems. Nevertheless, some problems in nature cannot be idealized. For example, the case of a non-straight crack front or the case when climatic variations are associated with a mechanical stress field.

Most of the studies carried out deal with two-dimensional case. The studies of the durability of structures based on bio-sourced materials request the development of specific tools for three-dimensional configurations.

In this context, our approach is to rewrite the M-integral formalism, starting from the very beginning with a three-dimensional analysis. The topic of this paper deals with the generalisation of the mixed mode M-integral formalism to a three-dimensional problem and its adaptability of the theta method for a finite element implementation. In order to complete fracture tools, this paper deals with a new 3D integral parameter allowing the fracture mode separation taking into account effect of anti-plane (mode III) and thickness during crack growth process. The first section recalls some integral parameters that we use in calculating the energy release rate for three-dimensional configuration around the crack front line. The development of the three-dimensional M-integral concept, based on a Noether's theorem, is presented and the numerical validation is proposed in the second section. Results are presented in terms of the energy release rate evaluations for mixed-mode configurations.

2. Analytical formulation

For plan problem and for static crack Rice (1968) [1] has defined A path independent integral which allows to compute energy release rate around the crack tip. For cracked linear elastic material, Rice [1] have used J-integral to compute energy release rate for curvilinear contour. J-integral takes the following notation:

$$J^{2D} = \int_{\Gamma} (W \cdot n_1 - (\sigma_{ij} \cdot n_j \cdot u_{i,1})) \cdot d\Gamma \quad (1)$$

Where W denotes the strain energy density, Γ is arbitrary curvilinear contour oriented by its normal vector, u_i is the displacement component and σ_{ij} is the stress component.

For mixed mode three-dimensional problem, the crack front line is defined as the intersection of two surface (figure 1).




Figure 1. Closed volume and surfaces integration domains for 2D and 3D case

element computation is realized with the software Cast3m, produced by French Energy Atomic Commission CEA.




Figure 4. Finite element mesh of MMCG specimen and Integral domain around the crack front line

Integral domain around the crack front line and Finite element mesh of MMCG specimen are shown in Fig. 4. The description of θ field around the crack front line is shown in Fig. 5. The θ field is equal to zero on outside surface, and 1 on inside surface.




Figure 5. θ field around the crack front line

In the follows, the first results of numerical study are exposed in order to observe the non-dependence domain for each fracture mode.




Figure 1. Average energy release rate vs. outside radius of θ field R_c

Numerical results validate the non-dependence of the integration domain.

4. Conclusion

This paper deals with a new formulation of the M-integral for the study of fracture process in element by taking into account three dimensional effects. A theoretical and numerical approach are established. In this case, the M integral is generalized to three-dimensional approach using the Lagrangian variation.

At this stages, more numerical investigations are necessary. Also, it will be necessary to extend the M integral in order to introduce hydrological and thermal effects for three dimensional problems [6].

5. Bibliographie

- [1] RICE James R., *A path independent integral and the approximate analysis of strain concentrations by notches and cracks*, Journal of Applied Mechanics, 1968, 379-386.
- [2] CHEN FMK., SHIELD RT., *Conservation laws in elasticity of J-integral type*, J. Appl. Mech. Phys., 28, 1977, 1–22.
- [3] MOUTOU PITTI Rostand, DUBOIS Frédéric, PETIT Christophe, SAUVAT Nicolas, POP Octavian, *A new M-integral parameter for mixed-mode crack growth in orthotropic viscoelastic material*, Eng. Fract. Mech., 2008, vol. 75, 4450–4465.
- [4] EL KABIR Soliman, MOUTOU PITTI Rostand, RECHO Naman, LAPUSTA Yuri, DUBOIS Frédéric, *Numerical study of crack path by MMCG specimen using M integral*, Journal of Fracture and Structural Integrity, 2016, 64-73.
- [5] DUBOIS Frédéric, PETIT Christophe, *Modelling of the crack growth initiation in viscoelastic media by the $G\theta_v$ -integral*, Engineering Fracture Mechanics, 2005, 2821-2836.
- [6] RIAHI Hassan, MOUTOU PITTI Rostand, DUBOIS Frédéric, CHATEAUNEUF Alaa, *Mixed-mode fracture analysis combining mechanical, thermal and hydrological effects in an isotropic and orthotropic material by means of invariant integrals*, Theoretical and Applied Fracture Mechanics, 2016, 424–434.