

**DSP PU 06****DIVIJA SPECIALTY POLYMERS**

Product Description: DSP PU 06 is a hydroxyl functional acrylic resin designed to crosslink at room temperature with poly Isocyanides.

Applications:

- Vehicle refinishes
- Heavy equipments
- Protective & marine
- General industrial
- Industrial wood finishes
- Suitable for acid resistant paints, durable metal coatings, in aircraft finishes, fiber glass components/boats, plastics, etc.

Advantage:

- High performance PU coating with excellent durability and all round performance.
- Excellent chemical & stain resistance.
- Good durability.
- Excellent adhesion.
- Long pot life.

Technical Specification:

Property	Unit	Value
Appearance	---	Clear Water White Viscous Liquid
Color	CGS	1 Max
Solid	%	60 ± 2%
Volatile	---	Xylene / Cello solve acetate
Viscosity @ 25°C	Poise	60 to 70
Acid value	Mg KOH/gm	10 Max.
% OH Content (on solid)	%	2.8
Hydroxyl equivalent weight (on solid resin)	---	approx. 600

Solubility: The solvents chosen for paints and lacquers based on DSP PU 06 should be free of water and should not contain groups that react with isocyanides. Esters and ketones are true solvents for this type of system and are recommended for usually used with aromatic hydrocarbon diluents.

Shelf Life: Under the above mentioned storage conditions the shelf life of the resin will be 12 months.

Packing: 200 Liter MS Drums.

Storage: DSP PU 06 should be stored indoors in the original containers in a dry place at temperature between 5°C and 30°C. Avoid exposure to direct sunlight or frost.

DISCLAIMER: The information contained in this sheet is accurate to the best of our knowledge .In View of conditions of use being totally beyond our control, customers should evaluate the data and make their own tests to determine the suitability of our product for their special use All our products are sold without warranty express or implied, and no liability can be accepted in respect of information and products.