

	DIVIJA SPECIALTY POLYMERS-KHUIDUS (AKLIJ).												
	SHORT OIL AIR DRYING / CHAIN STOPPED ALKYDS												
	PRODUCT CODE	Oil/Fatty Acid Type	Oil Length %	Non Volatile % ± 2%	Volatile	Viscosity Seconds @ 30° c PCB4	Acid value (Max) (Mg koh/gm)	Color (Gardner) Max.	Main Application Fields - Architectural / General industrials wood & metal				Application / Features
								Primer/Undercoat	Gloss Enamel	wood varnish	Protective & Marine		
DSP FDA 5027	SOFA	27	70	Xylene	120 -140 sec (100 gm Resin +50 gm Xylene)	15	6		OEM/ VR			GI	High quality, Non-yellowing, quick drying primers and top coats.
DSP FDA 5028	SOFA	28	70	Xylene	130 ± 20 sec (45% XL)	15	6		OEM/ VR		2K PU	GI	Air drying refinishes, low bake industrial stoving enamels, two pack polyurethane based coating
DSP FDA 5030	COFA	30	70	Xylene	40 - 60 (40% Xylene)	15	1	•	•	•			white baking enamels for refrigerators, washing machines, water filter and hospital appliances and as plasticizer for NC Lacquers wood coating. <i>bulbless clear NC Enamels and low bake industrial stoving enamels, two pack polyurethane based coating</i>
DSP FDA 5038	SOFA	38	70	Xylene	110 - 150 (50% XL)	12	5		OEM/ VR		2K PU	GI	Air drying refinishes, low bake industrial stoving enamels, two pack polyurethane based coating
ACRYLATED ALKYD RESIN - QUICK DRYING RESIN / SPECIALITY RESINS													
DSP ACRYKYD 5035	SOFA	45	60	Xylene	80 - 100 (50% XL)	10	4	Quick drying & good through Hardness without using any driers, Excellent water & chemical resistance, excellent gloss and gloss retention, good adhesion on metal surface and good flexibility.					
DSP APM 5036	Epoxy Silicon Modified Resin	NA	36 - 38	Xylene	60 - 70 (As such)	1	4	Ready to use aluminium paint medium, which is used for making High temperature silver paint upto 300°c					