

		DIVIJA SPECIALTY POLYMERS - KHUDUS (AKLUJ)						
		BUTYLATED MELAMINE FORMALDEHYDES						
PRODUCT CODE	POLYMER TYPE	Colour (G)	SOLVENT	% Non-volatile @ 110° c	Viscosity @25° (Poise)	Acid Value (mg koh/gm)	MTD TOLERANCE	Recommended Usages
DSP 51	Melamine Formaldehyde	1 Max.	Butanol	60 ± 2 %	8 to 12	1.0 Max.	1:3 to 4	Medium reactive butylated-type curing agent for stoving paints, roller coatings and foil inks. Mar-proof varnishes, acid catalysed wood finishes.
BUTYLATED UREA FORMALDEHYDES								
DSP 55	Urea formaldehyde	1 Max.	Butanol	65 ± 2 %	10 to 25	2 to 3	01:02	Fast curing at low temperature for screen & wood, epoxy and acid catalysed finishes.