

 DIVIJA SPECIALTY POLYMERS- KHUDUS, AKLUJ.							
NEW PRODUCT LIST							
POLYISOCYANATES HARDENERS FOR 2K PU SYSTEM							
PRODUCT CODE	TYPE	Colour (G)	Viscosity @25° (Poise)	Iso cyanate content%	% Non-volatile @ 110° c	Recommended Usages	Equivalent to /
DSP L 75-HV	Aromatic isocyanate	1 Max	16 +/- 4	13 ± 0.5	75 ± 2	Laminating adhesive, sealants chemicals and abrasion resistant coating, coating for sports goods, for air drying two pack Urethane coatings with acrylic polyol, short oil and chain stopped alkyd resin.	DESMADUR L 75
DSP L 51 BA	Aromatic isocyanate	1 Max	2 TO 4	8 ± 0.5	51 ± 2	Laminating adhesive, sealants chemicals and abrasion resistant coating, coating for sports goods, for air drying two pack Urethane coatings with acrylic polyol, short oil and chain stopped alkyd resin.	DESMADUR ULTRA IL 1351 BA
DSP N 75	Aliphatic isocyanate	1 Max	1.5 to 2.5	16.5 ± 1	75 ± 2	Good exterior durability, colour/gloss retention. Automobile repair, Heavy duty protective coating, wood, metal, plastic, synthetic leather, adhesives and film coating.	DESMADUR N 75
DSP Z 70	Aliphatic isocyanate(IPDI Based)	1 Max	8 to 14	12 ± 1	70 ± 2	Good exterior durability, colour/gloss retention. Automobile repair, Heavy duty protective coating, wood, metal, plastic, synthetic leather, adhesives and film coating.	DESMADUR 4470 MPA/XL
100 % SOLIDS PU ALIPHATHALIC HARDENER FOR PU POWDER COATING APPLICATIONS							
DSP BL 1530-100%	100 % Solids Aliphatic isocyanate	1 Max	Solids flakes	0.2 TO 0.8%	100%	DSP BL 1530 is a Polyisocyanate adduct used in combination with Hydroxy Functional Resins. Due to the e-Caprolactam blocked NCO-groups it is stable during processing up to the unblocking temperature of more than 160 °C. The Cross linker is delivered in the form of pellets.	VESTAGOAN BL 1530
BLOCKED ALIPHATHIC ISOCYANATES FOR PU STOVING APPLICATIONS CAN & COIL COATINGS							
DSP BL 1530-75%	75% BLOCKED ISOCYANATES FOR PU STOVING SYSTEM	1 Max	34 +/- 5	0.2 TO 0.8%	75 ± 2	DSP BL 1530 -75% is Blocked, aliphatic poly isocyanate based on HDI. Use to formulate lightfast, one-component polyurethane stoving coatings; as an additive in conventional stoving systems to improve flexibility and adhesion. Approximately 75 % in solvent naphtha® 100	DESMADUR BL 3175 SN