

 DIVIJA SPECIALTY POLYMERS- KHUDUS, AKLUJ. LIQUID REACTIVE POLYAMIDE HARDENER						
PRODUCT CODE	COLOR (Gardener)	Viscosity @25° (Poise)	Amine Value mg KOH/gm	AHEW (calcd)	PHR (190)	Recommended Usages
DSP POLYAMIDE 140	9 Max	40 to 80	350 to 400	97	52	Primer, intermediate, H8 Topcoat, Construction, Marine, Industrial. Polyamide for epoxy based castings, laminates and adhesives, solventless epoxy polyamide coatings.
DSP POLYAMIDE 160	10 Max	4 to 10	350 to 380	95	50	Flooring, Grouting, Sealant (long pot life), cost effective potting, encapsulation, laminating, adhesives.
CYCLOALIPHATIC AMINE ADUCTS						
PRODUCT CODE	COLOR (Gardener)	Viscosity @25° (Poise)	Amine Value mg KOH/gm	PHR (190)	Application Ratio	Recommended Usages
DSP ECA-428	1 Max	2 to 6	340 to 390	86	02:01	Industrial Flooring, tank lining, solvent free coatings & adhesives for concrete. Modified low viscosity amine curing agent used in combination with Liquid Epoxy cold curing/ ambient temperature. Used for Making table top, Menna work, Emissions jewellerys, Photo laminations.
DSP ECA-429	1 Max	1 to 2	440 to 460	60	03:01	Industrial Flooring, tank lining, solvent free coatings & adhesives for concrete. Modified low viscosity amine curing agent used in combination with Liquid Epoxy cold curing/ ambient temperature. Used for Making table top, Menna work, Emissions jewellerys, Photo laminations.
DSP ECA-432	1 Max	4 to 6	260 to 280	113	01:01	Industrial Flooring, tank lining, solvent free coatings & adhesives for concrete. Modified low viscosity amine curing agent used in combination with Liquid Epoxy cold curing/ ambient temperature. Used for Making table top, Menna work, Emissions jewellerys, Photo laminations.
DSP ECA-A1	2 Max	25 to 35	280 to 320	62	03:01	Industrial Flooring, tank lining, solvent free coatings & adhesives for concrete. Modified low viscosity amine curing agent used in combination with Liquid Epoxy cold curing/ ambient temperature. Used for Making table top, Menna work, Emissions jewellerys, Photo laminations.
DSP ECA-433	1 Max	1 to 2	440 to 460	60	03:01	Industrial Flooring, tank lining, solvent free coatings & adhesives for concrete. Modified low viscosity amine curing agent used in combination with Liquid Epoxy cold curing/ ambient temperature. Used for Making table top, Menna work, Emissions jewellerys, Photo laminations.
AROMATIC AMINE ADUCTS						
DSP ECA - 9080	Dark Brown	38 to 58	180 To 220	100	01:01	Very High Acid and chemical Resistance, water proofing (long pot life)
DSP ECA - 9085	Dark Brown	150 to 220	150 To 180	120	01:01.2	Very High Acid and chemical Resistance, water proofing (long pot life)
PHENALKAMINE EPOXY HARDENERS						
PRODUCT CODE	COLOR (Gardener)	Viscosity @25° (Poise)	Amine Value mg KOH/gm	AHEW (calcd)	PHR (190)	Recommended Usages
DSP PAH 9040	18 Max	20 to 30	290 to 350	110	60	Coating, Adhesives, Flooring, Construction, Marine, Tank Lining
DSP PAH 9041	18 Max	150 to 300	310 to 340	116	60	Tank lining, Adhesives, Wet concrete, Pipeline/Marine.

Lapox
428/
Camcure
2847

Cetepox
1312 FSH

Use for
Meena
kari work

water
white