



AMRITLAL CHEMAUX PVT. LTD.

**POLYISOCYANATES
PU RESINS**



POLYISOCYANATES HARDENERS FOR 2K PU SYSTEM

PRODUCT CODE	TYPE	Colour (G)	Viscosity @25° (Poise)	Isocyanate content%	% Non-volatile @ 110° c	Recommended Usages	Equivalent to /
ACL- L 75	Aromatic isocyanate	2 Max	2 TO 4	13 ± 0.5	75 ± 2	Laminating adhesive, sealants chemicals and abrasion resistant coating, coating for sports goods, for air drying two pack Urethane coatings with acrylic polyol, short oil and chain stopped alkyd resin.	DESMADUR L 75
ACL- L 51 BA	Aromatic isocyanate	1 Max	2 TO 4	8 ± 0.5	51 ± 2	Laminating adhesive, sealants chemicals and abrasion resistant coating, coating for sports goods, for air drying two pack Urethane coatings with acrylic polyol, short oil and chain stopped alkyd resin.	DESMADUR ULTRA IL 1351 BA
ACL- N 75	Aliphatic isocyanate	1 Max	2 to 3	16.5 ± 1	75 ± 2	Good exterior durability, colour/gloss retention. Automobile repair, Heavy duty protective coating, wood, metal, plastic, synthetic leather, adhesives and film coating.	DESMADUR N 75
ACL- Z 70	Aliphatic isocyanate (IPDI Based)	1 Max	8 to 14	12 ± 1	70 ± 2	Good exterior durability, colour/gloss retention. Automobile repair, Heavy duty protective coating, wood, metal, plastic, synthetic leather, adhesives and film coating.	DESMADUR 4470 MPA/XL

100 % SOLIDS PU ALIPHATHALIC HARDENER FOR PU POWDER COATING APPLICATIONS

ACL - BL 1530-100%	100 % Solids Aliphatic isocyanate	1 Max	Solids flakes	0.2 TO 0.8%	100%	ACL- BL 1530 is a Polyisocyanate adduct used in combination with Hydroxy Functional Resins. Due to the ε-Caprolactam blocked NCO-groups it is stable during processing up to the unblocking temperature of more than 160 °C. The Cross linker is delivered in the form of pellets.	VESTAGOAN BL 1530
--------------------	-----------------------------------	-------	---------------	-------------	------	--	-------------------

65% BLOCKED ALIPHATHIC ISOCYNATES FOR PU STOVING APPLICATIONS CAN & COIL COATINGS

ACL - BL 1530-65%	65% BLOCKED ISOCYANATES FOR PU STOVING SYSTEM	1 Max	60 to 80	0.2 TO 0.8%	65 ± 2	ACL- BL 1530 -65% is Blocked, aliphatic polyisocyanate based on HDI. Use to formulate lightfast, one-component polyurethane stoving coatings; as an additive in conventional stoving systems to improve flexibility and adhesion. Approximately 65 % in solvent naphtha 100	DESMADUR BL 3175 SN
-------------------	---	-------	----------	-------------	--------	---	---------------------

PU RESINS FOR INKS & ADHESIVES

PRODUCT CODE	TYPE	Colour (G) (Poise)	Viscosity @25° content%	Iso cyanate @ 110° c	% Non-volatile	Recommended Usages	Equivalent to /
ACL - PU 5244-75%	PU RESIN	2 Max	2 TO 4	13 ± 0.5	75 ± 2	"ACL -PU 5244 is a non-reactive, flexible urethane polymer, designed for use in conjunction with nitro cellulose in the manufacturing of alcohol soluble/Dilatable flexographic inks and clear lacquers. ACL PU 5244 supplied is approximately 75% in ethyl acetate.ACL- PU 5244 will impart excellent adhesion to numerous flexible films such as polyethylene, polypropylene, cellulose and polyester. Resistance to blocking, heat, Deepfreeze, oils, fats, water and tarnishing is superior." Use For Inks & clear Lacquers	
ACL - PU 60 - 75%	PU RESIN	1 Max	2 TO 4	13 ± 0.5	75 ± 2	Laminating adhesive, sealants chemicals and abrasion resistant coating, coating for sports goods. Use For Lamination Adhesives manufacturing	