



AMRITLAL CHEMAUX PVT. LTD.

ACRYLIC RESINS



2K HYDROXYL FUNCTIONAL ACRYLICS

PRODUCT CODE	% OH on solids	Non Volatile %+- 2	Volatile	Viscosity in poise @ 25° c	Acid value Max (mg/koh/gm)	MAIN APPLICATION FIELDS					Application / Features	Equivalent to /	
						Vehicle Refinishes	Heavy Equipment (A.C.E)	Protective & Marine	General Industrial	Industrial Wood finishes			
ACCRYL 5005	1.55	55	Xylene	25 - 35	10	•	•	•	•	•	Rapid drying good adhesion to galvanised steel	Synocure 862x -55	
ACCRYL 5006	2.8	60	Xylene / Cellosolve Acetate	60 - 70	10	•	•	•	•	•	High Performance PU Coating with excellent durability and all round performance	ARKEMA Syn 867 s	RPL Replakryl 929
ACCRYL 5007	2.1	60	Xylene / Cellosolve Acetate	35 - 50	10		•	•	•		High Performance PU Coating with excellent durability and all round performance	Synocure 870s-60	RPL Replakryl 939
ACCRYL 5009	2.1	60	Xylene / Cellosolve Acetate	220 - 240	10			•	•		PU Coating with excellent flexibility and weathering property compatible with CAB	Synocure 868s-60	
ACCRYL 5010	2.1	60	Xylene	40 - 50	5	•	•		•	•	Auto-Refinishing, wood coating, ind-coating, chemical resistant & High performance PU coating.	Synocure 870s-60	DRC- Drokryl 7864
ACCRYL 5012	4.5	60	Xylene / Butyl acetate	80 - 120	10	•	•		•	•	Premium clear coat for vehicle refinish and wood coating application.	Macrynl sm 510, syn 851 s- 60	

HIGH SOLIDS - 2K HYDROXYL FUNCTIONAL ACRYLICS

ACCRYL 5008	2.3	70	Xylene	40% xylene 30 to 60 sec(FCB4 30C)	8	•	•	•	•		High solids and economical for base/ top coat automotive finishes	Macrynl 8649-70	
ACCRYL 5008-HC	2.3	70	Xylene / Cellosolve Acetate	40% xylene 30 to 60 sec(FCB4 30C)	10	•	•		•		High solids and economical for base/ top coat automotive finishes	Macrynl 8649-70	
ACCRYL 5011	2.8	70	Xylene / Cellosolve Acetate	80 - 100	10	•	•	•	•		High Performance PU Coating with excellent durability and all round performance	Macro 8064, idecryl 8064	
ACCRYL 5013	4.5	70	Butyl acetate	40 - 60	10	•	•	•	•		Recommended for high performance industrial, vehicle refinishing & OEM Applications	Macrynl sm 515, 70BAC, syn 9299BA-70	
ACCRYL 5014	2.1	70	Xylene / Cellosolve Acetate	35 - 50	5	•	•	•	•		Air drying and force drying compatible with all types of acrylic resins, interior on metal furniture, agriculture machinery, Domestic appliances. Auto-refinishing, wood coatings, ind-coating, chemical resistant & high performance PU coating	Replakryl 940	

THERMOSETTING ACRYLIC RESIN / TSA RESIN

ACCRYL 5015	1.55	60	Xylene / Cellosolve Acetate	25 - 35	15 - 20	Main Application - OEM & GI CLEAR COAT & MONOCOAT					Low temperature curing paints & lacquers for auto body enamels & domestic appliance finishing.	Synocryl 826s-& 829 s- 60%	
ACCRYL 5016	2.8	60	Xylene / Cellosolve Acetate	10 - 20	15	Main Application - OEM & GI CLEAR COAT & MONOCOAT					Low temperature curing paints & lacquers for auto body enamels & domestic appliance finishing.	Macro TSA 1003- 60%	

THERMOPLASTIC ACRYLIC RESIN

PRODUCT CODE	Polymer	Non Volatile %+- 2	Volatile	Viscosity in poise @ 25° c	Acid value Max (mg/koh/gm)	Main Application Fields					Application / Features	Equivalent to /	
						Architecture	Vehicle Refinishes	Home Appliance	Protective & Marine	General Industrial			
ACCRYL 5001	Copolymer	40	Aromatic solvent 100	10 - 18	10	•	•		•	•	Versatile acrylic resin for decorative & industrial coatings, good durability, glass & color retention. Can also be used as modifier for chlorinated rubber paint. very high quality flexible air drying finishes with excellent colour, gloss & durability	Synocryl 874 N 40%	
ACCRYL 5002	Copolymer	45	Xylene	10 - 15	10		V / R			Aerosol	Versatile acrylic resin for decorative & industrial coatings, good durability, glass & color retention. Can also be used as modifier for chlorinated rubber paint. very high quality flexible air drying finishes with excellent colour, gloss & durability	Synocryl 874 x- 45%	
ACCRYL 5004	Copolymer	60	Xylene	200 - 230	15	•	•	•	•	•	Excellent flexibility, pigment dispersion and plasticizer. high gloss and gloss retention. Good around weathering properties. Good for exterior concrete applications.	Macro - TPA 696	
ACCRYL 5003	Copolymer	50	Xylene	40 - 60	10	•	•	•		•	Main application is for general purpose masonry, decorative coatings, aerosol paints. TPA exhibit good gloss, color retention, setting properties, good outdoor durability, excellent soap and detergent resistant.	Hitech A4010 x - 50%	