



AMRITLAL CHEMAUX PVT. LTD.

EPOXY HARDNER & ADHESIVES

EPOXY HARDENER

REACTIVE CYCLOALIPHATIC POLYAMINES

PRODUCT CODE	COLOR (Gardener)	Viscosity @25° (Poise)	Amine Value mg KOH/gm	AHEW (calcd)	Application Ratio	Recommended Usages	Equivalent to /
ACL -ECH-428	1 Max	2 to 6	340 to 390	86	2:01	Industrial Flooring, tank lining, solvent free coatings & adhesives for concrete. Modified low viscosity amine curing agent used in combination with Liquid Epoxy cold curing/ ambient temperature. Used for Making table top, Mena work, Imitations jewelleryes, Photo laminations.	Lapox 428/ Camcure 2847
ACL -ECH-429	1 Max	1 to 2	440 to 460	60	3:01	Industrial Flooring, tank lining, solvent free coatings & adhesives for concrete. Modified low viscosity amine curing agent used in combination with Liquid Epoxy cold curing/ ambient temperature. Used for Making table top, Mena work, Imitations Jewelleryes, Photo laminations.	
ACL -ECH-432	1 Max	4 to 6	260 to 280	113	1:01	Industrial Flooring, tank lining, solvent free coatings & adhesives for concrete. Modified low viscosity amine curing agent used in combination with Liquid Epoxy cold curing/ ambient temperature. Used for Making table top, Mena work, Imitations Jewelleryes, Photo laminations.	Cetepox 1312 FSH
ACL -ECH-A1	2 Max	25 to 35	280 to 320	62	3:01	Industrial Flooring, tank lining, solvent free coatings & adhesives for concrete. Modified low viscosity amine curing agent used in combination with Liquid Epoxy cold curing/ ambient temperature. Used for Making table top, Mena work, Imitations Jewelleryes, Photo laminations.	

STANDARD EPOXY ADHESIVE (FIX - TITE)

PRODUCT CODE	POLYMER TYPE	Colour (G)	SOLVENT	% Non-volatile @ 110° c	RESIN Viscosity @25° (Poise)	HARDENER Viscosity @25° (Poise)	APPLICATION / MIXING RATIO	Application Temp. ° c	Service Temp. ° c	Recommended Usages	Equivalent to
ACL - FIX - TITE	EPOXY ADHESIVES	WATER WHITE & PALE YELLOW	SOLVENT FREE	100%	80 to 120	30 to 40 POISE	1:1 (By weight)	From +10° C to +35° C	From -20° C to +100° C	"Fix - Tite is RAPID, CLEAR, HIGH-STRENGTH EPOXY ADHESIVE. Epoxy Resin and Epoxy Hardener is a rapid-setting, two-component epoxy adhesive with a convenient 1:1 Resin-to-Hardener Mix Ratio. The product generates strong bonds on a wide variety of substrates in a short period of time. No special handling or application techniques are required. ACL Fix - Tite Resin & Hardener epoxy adhesive is a multi-purpose, viscous material that is suitable for bonding a variety of materials including metal, ceramic, and wood. The electrically insulating adhesive is easy to apply either manually by spatula and stiff brush or mechanically with meter/mix and coating equipment. ACL Resin/Hardener epoxy adhesive cures at temperatures from 68°F (20°C) to 356°F (180°C) with no release of volatile constituents."	Araldite / Bond Tite

AQUA SEAL - EPOXY GROUT / WATER PROOFING TANKS / CRACK SEAL

PRODUCT CODE	POLYMER TYPE	Mixed Material Colour (G)	SOLVENT	% Non-volatile @ 150° c	RESIN Viscosity @25° (Poise)	HARDENER Viscosity @25° (Poise)	APPLICATION / MIXING RATIO	Application Temp. ° c	Service Temp. ° c	Recommended Usages	Equivalent to
ACL -AQUA SEAL	EPOXY GROUT SYSTEM	Gray	solvent free	100%	80 to 120 Poise	2 to 3 poise	Resin 300 gm + Hardener 100 gm + Filler 600 gms	From +10° C to +35° C	From -20° C to +100° C	"ACL - Aqua Seal is formulated for waterproofing as a grouting material it is a low viscosity liquid which react with water in a controlled manner to form a swelling resilient adhesive solid in densities and strength. When impregnated under pressure into leakage structures, terraces, tank, tunnel, dam, canals, etc. After curing it gives permanent polymer barrier is formed. The liquid retains its initial low viscosity upon contacting water allowing it to flow without dilution. Once the Aqua Seal water reaction commences, the grout expands penetrating in to its surrounding and quickly cures to a tough, adhesive solid to repel the influence of underground seepage flow and solidify the objectives Ground which is unaffected by corrosive environment."	

TILES COATING RESIN & HARDENER

PRODUCT CODE	POLYMER TYPE	Colour (G)	SOLVENT	% Non-volatile @ 110° c	RESIN Viscosity @25° (Poise)	HARDENER Viscosity @25° (Poise)	APPLICATION RATIO	Recommended Usages
ACL - TILE MASTER RESIN & HARDENER	EPOXY RESIN & HARDENERS	WATER WHITE & PALE YELLOW	SOLVENT FREE	100%	24 to 26	13 TO 15	2: 1 (By weight)	"ACL TileMaster Resin & Hardener is a crystal clear epoxy based polymer Adduct. Of gloss and adhesion improver are suitable for 3D floorings can apply on concrete, Stone, Tiles coatings, wood and ceramics and laminated sheets specially developed coating are transparent and colored application."