

**DSP 5081- WAXSOL****DIVIJA SPECIALTY POLYMERS.**

Product Description: DSP 5081 is Wax dispersion on the basis of an EVA copolymer wax for solvent-borne effect coating systems. Improves the orientation of effect pigments and reduces settling in the container.

Applications:

- DSP 5081 is recommended for solvent-borne base coats and one-coat metallic top coats in industrial coatings.

Advantage:

The additive improves the orientation of effect pigments (e.g. aluminium, mica) and enhances the flip-flop effect. Short wave defects are minimized and levelling of the subsequent clear coat layer is improved. Settling in the container is also reduced.

Technical Specification:

Property	Unit	Value
Appearance	---	Milky White low Viscous Liquid
Color	CGS	Milky white
Solid	%	10 ± 1%
Volatile	---	Xylene / Butyl acetate
Viscosity @ 25°C	Poise	1 to 2
Particle size	Hegman	7+

Recommended Levels

30 % additive (as supplied) based upon the solid binder. The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The wax additive must be homogenized before use with a dissolver (4 m/s) and then added to the binder Solution under agitation. In systems with CAB, the CAB solution must first be incorporated homogeneously In the binder solution at high shear forces (> 5 m/s) before the stirred wax additive, the effect pigment Slurry and the solvent can be added under agitation.

Shelf Life: Under the above mentioned storage conditions the shelf life of the resin will be 12 months.

Packing: 200/50/20 Liter MS Drums.

Storage: DSP 5081 Temperature sensitive. Do not store or transport above 35 °C. Stir before use.

DISCLAIMER: The information contained in this sheet is accurate to the best of our knowledge .In View of conditions of use being totally beyond our control, customers should evaluate the data and make their own tests to determine the suitability of our product for their special use All our products are sold without warranty express or implied, and no liability can be accepted in respect of information and products.