

**DSP PU 09****DIVIJA SPECIALTY POLYMERS**

Product Description: DSP PU 09 is a hydroxyl functional acrylic resin designed to crosslink at room temperature with poly Isocyanides. Also used for base coat binder 1k system.

Applications:

- Protective & marine
- General industrial
- Base coat binder 1 k system

Advantage:

- PU Coatings with excellent flexibility
- Weathering property
- Compatible with CAB.

Technical Specification:

Property	Unit	Value
Appearance	---	Clear Water White Viscous Liquid
Color	CGS	1 Max
Solid	%	60 $\pm$ 2%
Volatile	---	Xylene / Cello solve acetate
Viscosity @ 25°C	Poise	280 to 320
Acid value	Mg KOH/gm	10 Max.
% OH Content (on solid)	%	2.1
Hydroxyl equivalent weight (on solid resin)	---	approx. 800

Solubility: Compatible with CAB, Xylene, Cello solve acetate, butyl acetate.

Shelf Life: Under the above mentioned storage conditions the shelf life of the resin will be 12 months.

Packing: 200 Liter MS Drums.

Storage: DSP 09 should be stored indoors in the original containers in a dry place at temperature between 5°C and 30°C. Avoid exposure to direct sunlight or frost.

DISCLAIMER: The information contained in this sheet is accurate to the best of our knowledge .In View of conditions of use being totally beyond our control, customers should evaluate the data and make their own tests to determine the suitability of our product for their special use All our products are sold without warranty express or implied, and no liability can be accepted in respect of information and products.