

**DSP N 75****DIVIJA SPECIALTY POLYMERS**

Product Description: DSP N 75 is an Aliphatic Polyisocyanate resin based on Hexamethylene Diisocyanate (HDI) and dissolved in N-Butyl Acetate.

Applications & Advantage:

- Automobile repair
- Heavy duty protective coating
- Wood, metal, plastic & synthetic leather
- Adhesives and film coatings
- Good exterior durability
- Good color & gloss retention

Technical Specification:

Property	Unit	Value
Appearance	---	Clear Viscous Liquid
Color	CGS	Water white
Solid @100° C	%	75 ± 2%
Volatile	---	Butyl Acetate.
Viscosity @ 25°C	CPS	150 To 250
NCO Content	%	16.5 ± 0.5
Density @ 25° c	g/ml	1.10 ± 0.05
Monomer content	%	< 0.5
Equivalent weight	---	260 Approx.

Solubility: DSP N 75 Polyisocyanate can be diluted with ethyl acetate, butyl acetate, PM acetate, toluene, xylene and most Ketones. It is insoluble in aliphatic hydrocarbons. Since DSP N 75 is sensitive to moisture, polyurethane grade solvents with moisture content less than 500 ppm (0.05%) should be used. When diluting DSP, the solids content should not be lower than 35%; otherwise turbidity and precipitation may occur. Alcohols and amines should not be used, as they react with DSP N 75 Polyisocyanate.

Compatibility: - DSP N 75 is compatible with a variety of other Polyisocyanates and as well as the aromatic Polyisocyanates. Generally, good compatibility is observed with most polyesters, hydroxyl-functional acrylics and Polyether's.

Storage: DSP N 75 should be stored in tightly sealed original containers and protected from moisture, heat, and foreign materials. Storage at higher temperatures will result in increase of colour and viscosity. Storage at significant Lower temperatures will result in solidification. This solidification is reversible by briefly heating the product without adversely affecting the quality of the product. Recommended storage temperature is 0°-30°C.

TECHNICAL DATA SHEET

Handling instructions: - This product contains reactive HDI polyisocyanate/prepolymer and/or monomeric HDI and should only be handled using appropriate protective measures. Please review this product's Material Safety Data Sheet for a summary of such protective measures. These products are suitable only for and should only be sold for use by industrial or trade (commercial) professionals. These products are not suitable for Do-It-Yourself applications.

Shelf Life: Under the above mentioned storage conditions the shelf life of the resin will be 6 months.

Health and Safety Information: - Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling this product. Before working with this product, you must read and become familiar with the available information on its risks, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., safety data sheets and product labels.

Packing: 25/210 kg MS Drums.

DISCLAIMER: The information contained in this sheet is accurate to the best of our knowledge. In View of conditions of use being totally beyond our control, customers should evaluate the data and make their own tests to determine the suitability of our product for their special use. All our products are sold without warranty express or implied, and no liability can be accepted in respect of information and products.
