

**DSP L 75-HV****DIVIJA SPECIALTY POLYMERS**

Product Description: DSP L 75-HV is an aromatic poly Isocyanate based on toluene di isocyanate (TDI). It can be used in combination with various grades or other hydroxyl-bearing substances to formulate two component polyurethane coatings and adhesives. DSP L 75-HV supplied is approximately 75% in ethyl acetate.

Applications & Advantage:

- For Air Drying Two Pack Urethane coatings with Acrylic polyol
- Short oil & chain stopped alkyd resin curing
- Laminating adhesive
- Sealants chemicals
- Abrasion resistant coatings
- Coating for sports goods
- Good gloss retention.

Technical Specification:

Property	Unit	Value
Appearance	---	Clear Viscous Liquid
Color	CGS	Water white
Solid @100° C	%	75 ± 2%
Volatile	---	Ethyl acetate
Viscosity @ 25°C	CPS	1600 + / -400 CPS
NCO Content	%	13.5 ± 0.5
Density @ 25° c	g/ml	1.15 ± 0.05
Monomer content	%	< 0.5
Equivalent weight	---	320 Approx.

Solubility: DSP L 75-HV In general has good compatibility with esters such as ethyl acetate, butyl acetate and 1-methoxypropylacetate-2 and aromatic hydrocarbons such as toluene, xylene, c-09 & c-10. However, the solutions formed must be tested for their storage stability. The product is not compatible with aliphatic. Alcohols react with L 75-HV and therefore cannot be used. Prolonged storage of a solution with low binder content may result in turbidity and sedimentation. Only PU grade solvents should be used (< 0.05% water). The solvent should not contain reactive groups.

Compatibility: - In general, DSP L 75-HV is compatible with many polyesters and Polyacrylates, as well as with other grades.

Storage: should be stored in tightly sealed original containers and protected from moisture, heat, and foreign materials. Storage at higher temperatures will result in increase of colour and viscosity. Storage at significant Lower temperatures will result in solidification. This solidification is reversible by briefly heating the product without adversely affecting the quality of the product. Recommended storage temperature is 0°-30°C.

Shelf Life: Under the above mentioned storage conditions the shelf life of the resin will be 9 months.

Safety: - Highly flammable. Harmful by inhalation. Irritating to the eyes. May cause sensitization by inhalation. Repeated exposure may cause skin dryness or cracking.

Packing: 25/225 kg MS Drums.

DISCLAIMER: The information contained in this sheet is accurate to the best of our knowledge .In View of conditions of use being totally beyond our control, customers should evaluate the data and make their own tests to determine the suitability of our product for their special use All our products are sold without warranty express or implied, and no liability can be accepted in respect of information and products.