

58610 Quartz Powder, medium, ca. 44 µm

Sieve Residue

(according to DIN 66165)

Mesh Size (µm)	Residue
> 71	--
> 63	--
> 40	2 %
< 40	98 %

Technical Data

Luminosity A (DIN 5033-6)	82.0
Oil absorption (DIN EN ISO 787-5)	20 g / 100 g
Density (DIN EN ISO 787-10)	2.65 g/cm ³
Bulk density (DIN 53468)	0.90 g/cm ³

Chemical Analysis

(according to DIN 51001)

SiO ₂	98.50 %
Al ₂ O ₃	0.70 %
Fe ₂ O ₃	0.04 %
TiO ₂	0.06 %
CaO + MgO	0.10 %
Na ₂ O	0.01 %
K ₂ O	0.30 %
Ignition loss	0.30 %

Chemical analysis with regard to ROHS Regulation 2002/95/EU:

Pb: 0% - Hg: 0% - Cd: 0% - Cr6: 0% - PBB: 0% - PBDE: 0%