

MONOFILAMENT REINFORCED PACKAGING TAPE

PET-GLASS FIBRE LAMINATE / HOT MELT ADHESIVE

PRODUCT CODE

DT7143



Description	DEON® DT7143 - MONOFILAMENT REINFORCED PACKAGING TAPE Monofilament reinforced tape with polyester film and longitudinal glass fibre filaments, coated with hot melt adhesive, designed for high-strength bundling, strapping, and heavy-duty packaging applications where tear resistance and dimensional stability are critical.																																										
Features	• High Tensile Strength (≥ 120 N/cm) • Good Adhesion to Metal, Carton & Plastic Surfaces • Low Elongation (≤ 5%) for Stable Load Holding • Longitudinal Filament Reinforcement for Tear Resistance																																										
Application	• Steel Coil & Metal Bundle Wrapping • Appliance & Industrial Equipment Securing for Transit • Heavy-Duty Export Carton Reinforcement • Container Cover Sealing & Load Unitising																																										
Technical Properties	<table><tr><th>Product Characteristics</th><th>UOM</th><th>Typical Values</th><th>Test Method</th></tr><tr><td>Backing Material</td><td>-</td><td>PET / Glass Fibre Laminate</td><td>-</td></tr><tr><td>Thickness (Customizable)</td><td>µm</td><td>120 ± 0.005</td><td>ASTM D1000</td></tr><tr><td>Width (Customizable)</td><td>mm</td><td>48</td><td>ASTM D1000</td></tr><tr><td>Length (Customizable)</td><td>m</td><td>50</td><td>-</td></tr><tr><td>Adhesive</td><td>-</td><td>Synthetic Hot Melt</td><td>-</td></tr><tr><td>Adhesive Coating</td><td>-</td><td>Single - sided</td><td>-</td></tr><tr><td>Adhesion to Steel (min)</td><td>N/cm</td><td>8.0</td><td>ASTM D1000</td></tr><tr><td>Tensile Strength (min)</td><td>N/cm</td><td>120</td><td>ASTM D1000</td></tr><tr><td>Elongation at Break</td><td>%</td><td>5</td><td>ASTM D1000</td></tr></table>			Product Characteristics	UOM	Typical Values	Test Method	Backing Material	-	PET / Glass Fibre Laminate	-	Thickness (Customizable)	µm	120 ± 0.005	ASTM D1000	Width (Customizable)	mm	48	ASTM D1000	Length (Customizable)	m	50	-	Adhesive	-	Synthetic Hot Melt	-	Adhesive Coating	-	Single - sided	-	Adhesion to Steel (min)	N/cm	8.0	ASTM D1000	Tensile Strength (min)	N/cm	120	ASTM D1000	Elongation at Break	%	5	ASTM D1000
Product Characteristics	UOM	Typical Values	Test Method																																								
Backing Material	-	PET / Glass Fibre Laminate	-																																								
Thickness (Customizable)	µm	120 ± 0.005	ASTM D1000																																								
Width (Customizable)	mm	48	ASTM D1000																																								
Length (Customizable)	m	50	-																																								
Adhesive	-	Synthetic Hot Melt	-																																								
Adhesive Coating	-	Single - sided	-																																								
Adhesion to Steel (min)	N/cm	8.0	ASTM D1000																																								
Tensile Strength (min)	N/cm	120	ASTM D1000																																								
Elongation at Break	%	5	ASTM D1000																																								
Available Colours	Yellowish																																										
Storage & Usage Conditions	Store at room temperature, away from direct sunlight, heat, and moisture. Shelf life is six months from the date of shipment when stored under standard conditions (21°C, 50% RH). Ensure the application surface is clean, dry, and free from grease and oil. A trial application is recommended to confirm suitability for the intended use.																																										
Available Formats	Standard cut rolls and jumbo roll formats for slitting and conversion																																										

