

PRINCIPALES UTILISATIONS

Eau de mer dans zone non immergée et zone non explosive

DOCUMENTS DE REFERENCE

-

FOURNISSEUR FABRICANT

FUTURE PIPE INDUSTRIES Gamme Wavistrong Pipes systems

ETAT DE LIVRAISON

-

DOCUMENTS DE CONTROLE

Document de contrôle suivant NF EN 10-204 type 2.1, type 2.2, type 3.1, type 3.2 si spécifié sur la commande.

MATERIEL AVEC APPROBATION

Certificat d'Approbation de type BV N° 5583 et DNV N° K-5924

MATIERE TRAITEMENT DE SURFACE

STRATIFIE VERRE RESINE

Paroi interne riche en résine époxy renforcée par un voile de verre ou de polyester 0,5mm. Paroi effective:fibres de verre imprégné de résine époxy, épaisseur en fonction de la pression Paroi extérieure:couche de résine époxy 0,3mm

CHARACTERISTIQUES

Tuyauterie en GRP répondant à la résolution IMO A.753(18) L3.

Résistance au feu pendant 1/2h à l'état plein.

Standard utilisable pour les classes PN10 uniquement du DN 40 au DN150 (plage à ajuster en fonction des DN présents dans ce standard).

MAIN USES

Sea water pipes in no submerged spaces and no explosive spaces

REFERENCE DOCUMENTS

-

SUPPLIER MANUFACTURER

FUTURE PIPE INDUSTRIES Gamme Wavistrong Pipes systems

DELIVERY STATUS

-

CONTROL DOCUMENTS

Certificate according to NF EN 10204 type 2.1, type 2.2, type 3.1, type 3.2 if specified on the order

MATERIAL WITH APPROVAL

Certificate of Type Approval : BV N° 5583 / DNV N°K-5924

MATERIAL SURFACE TREATMENT

STRATIFY GLASS RESIN


Wall structure:resin-rich inner layer reinforced with glass or linear polyester non-woven Th0,5mm. Reinforced wall:glass reinforcement with amine cured EPOXY resin, Th depends on pressure. Wall has epoxy resin topcoat 0,3mm

CHARACTERISTICS

Pipe in GRP answered resolution A.753(18) L3.

Fire endurance for 1/2h full of water.

Standard used for PN10 classes only from DN 40 to DN 150 (range adjust for DN present in this standard).



Embout femelles coniques TB/TB

Pour assemblage conique/conique par collage (T5)

Référence Objet	DN1 (mm)	DN2 (mm)	TH1 (mm)	TH2 (mm)	Weight (kg)	Water Weight (kg)	Work Diam 1 WD1 (mm)	Work Diam 2 WD2 (mm)	Pipe Length (mm)	F1 TO F2 (mm)	SCH1 (-)	Pressure (-)	L (mm)	B (mm)	C (mm)	D (mm)
5000006674	450	350	8.1	6.5	33	51.52	466.2	363	410	685	15.7	20	410	137.5	15	15
5000006676	450	400	8.1	7.3	26	31.21	466.2	414.6	220	515	15.7	20	220	147.5	15	15
5000006678	500	400	8.9	7.3	42	65.21	517.8	414.6	410	715	17.3	20	410	152.5	15	15
5000006680	500	450	8.9	8.1	34	38.98	517.8	466.2	220	550	17.3	20	220	165	15	15
5000006683	600	450	10.6	8.1	79	129.88	621.2	466.2	600	965	20.6	20	600	182.5	15	15
5000006685	600	500	10.6	8.9	67	97.41	621.2	517.8	410	785	20.6	20	410	187.5	15	15